WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL





## Wachine Id VOLVO L70H 624045


Rear Axle

{not provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		VCP0008459		
	Sample Date		Client Info		17 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>500	75		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	2		
	Nickel	ppm	ASTM D5185m		2		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	2		
	Lead	ppm	ASTM D5185m	>50	<1		
	Copper	ppm	ASTM D5185m	>120	107		
	Tin	ppm	ASTM D5185m	>20	12		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	<u>~50</u>	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		1		
	Water	PP	WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
	Boron	ppm	ASTM D5185m		20		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		3		
	Magnesium	ppm	ASTM D5185m		3		
	Calcium	ppm	ASTM D5185m		757		
	Phosphorus	ppm	ASTM D5185m		547		
	Zinc	ppm	ASTM D5185m		661		
	Sulfur	ppm	ASTM D5185m		1554		
	Visc @ 40°C	cSt	ASTM D445		43.2		











Certificate L2367

Laboratory Sample No.

: VCP0008459 Lab Number : 06216169 Unique Number : 11089033 Test Package : CONST

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 20 Jun 2024 **Tested** : 21 Jun 2024

Diagnosed : 23 Jun 2024 - Don Baldridge **ALTA EQUIPMENT COMPANY** 

8750 PHILIPS HWY JACKSONVILLE, FL

US 32256 Contact: TECHNICIAN ACCOUNT

catherine.anastasio@wearcheck.com T:

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (904)737-1260