

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



120556-1216 LIEBHERR LH50M 120556-1216

**Rear Left Wheel Hub** 

Rear Left Wheel Hub Fluid GEAR OIL SAE 80W90 ( GA	L)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		DJJ0022476	DJJ0022495	DJJ0022513
	Sample Date		Client Info		24 May 2024	08 Mar 2024	03 Jan 2024
	Machine Age	hrs	Client Info		9944	9578	9096
	Oil Age	hrs	Client Info		0	0	0
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	>325	41	29	26
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>3	<1	<1	<1
	Nickel	ppm	ASTM D5185m	>2	0	0	0
	Titanium	ppm	ASTM D5185m	>4	<1	0	<1
	Silver	ppm	ASTM D5185m	>2	0	0	0
	Aluminum	ppm	ASTM D5185m	>10	2	2	2
	Lead	ppm	ASTM D5185m	>3	0	0	0
	Copper	ppm	ASTM D5185m	>70	11	9	10
	Tin	ppm	ASTM D5185m	>2	0	0	<1
	Vanadium	ppm	ASTM D5185m		0	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>70	2	2	2
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2	<1	1
	Water		WC Method	>0.2	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	LIGHT	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORMI
	Odor	scalar	*Visual	NORML	NORML	NORML	NORMI
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	2	2	0
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	58	81	106
	Barium	ppm	ASTM D5185m	200	0	0	0
	Molybdenum	ppm	ASTM D5185m	12	0	0	<1
	Manganese	ppm	ASTM D5185m		1	<1	<1
	Magnesium	ppm	ASTM D5185m	12	3	1	0
	Calcium	ppm	ASTM D5185m	150	43	58	62
	Phosphorus	ppm	ASTM D5185m	1650	1654	1367	1219
	Zinc	ppm	ASTM D5185m		32	33	2
	Sulfur	ppm	ASTM D5185m	22500	22208	22622	20680


Visc @ 40°C


151


ASTM D445 143


145

141











Certificate L2367

Laboratory Sample No.

Lab Number : 06216194

: DJJ0022476 Unique Number : 11089058 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 20 Jun 2024 **Tested** 

Diagnosed

: 21 Jun 2024 : 21 Jun 2024 - Wes Davis

RIVER METALS RECYCLING - DECATUR FACILITY 4301 IVERSON BLVD

TRINITY, AL US 35673 Contact: RYAN BOWDEN

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: