WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL




KEMP QUARRIES / RIVER VALLEY OZARK

WL033

Rear Right Final Drive

MOBIL MOBILTRANS HD 50 (GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		PCA0109135	PCA0069710	PCA0069759
	Sample Date		Client Info		13 Jun 2024	15 Mar 2024	10 Oct 2023
	Machine Age	hrs	Client Info		43181	42691	42265
	Oil Age	hrs	Client Info		323556	323556	323556
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				NORMAL	NORMAL	NORMAL
WEAR	Iron	ppm	ASTM D5185m	>800	205	196	66
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	0	<1	<1
	Nickel	ppm	ASTM D5185m	>5	0	<1	0
	Titanium	ppm	ASTM D5185m	>15	<1	<1	<1
	Silver	ppm	ASTM D5185m	>2	0	0	0
	Aluminum	ppm	ASTM D5185m	>75	3	3	2
	Lead	ppm	ASTM D5185m	>10	<1	<1	<1
	Copper	ppm	ASTM D5185m	>75	5	5	2
	Tin	ppm	ASTM D5185m	>8	2	2	1
	Vanadium	ppm	ASTM D5185m		0	<1	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>400	20	20	19
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3	2	<1
	Water		WC Method	>0.2	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	MODER	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2	0	2
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		2	0	0
	Barium	ppm	ASTM D5185m		0	1	0
	Molybdenum	ppm	ASTM D5185m		0	1	0
	Manganese	ppm	ASTM D5185m		2	2	1
	Magnesium	ppm	ASTM D5185m		16	13	15
	Calcium	ppm	ASTM D5185m		3072	3598	3163
	Phosphorus	ppm	ASTM D5185m		945	944	821
	Zinc	ppm	ASTM D5185m		1136	1162	1124
	Sulfur	ppm	ASTM D5185m		4721	4700	4004
	Visc @ 40°C	cSt	ASTM D445	195	149	169	176







Certificate L2367

Laboratory Sample No.

Lab Number

: 06216389 Unique Number : 11089253 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : PCA0109135 Received : 20 Jun 2024

Tested : 21 Jun 2024 : 21 Jun 2024 - Wes Davis Diagnosed

Kemp Quarries - River Valley - Ozark 9446 N Hwy 309

Ozark, AR US 72949

Contact: OZARK NOTIFICATIONS ozark@rivervalleyquarries.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: F: