WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

01 (S/N 46816787)

Diesel Engine

DIESEL ENGINE OIL SAE 40 (--- LTR)

DIESEL ENGINE OIL SAE 40 (LTR)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TESSIMETES/TTOT	Sample Number		Client Info		CU0023375		
Resample at the next service interval to monitor.	Sample Date		Client Info		11 Jun 2024		
	Machine Age	kms	Client Info		147374		
	Oil Age	kms	Client Info		0		
	Filter Age	kms	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status		Onorte into		NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	12		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	<1		
	Nickel	ppm	ASTM D5185m	>4	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m	>20	3		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	4		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	17		
	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol	%	*ASTM D2982		NEG		
	Soot %	%	*ASTM D7844	>3	0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	7.2		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	20.6		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		1		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		160		
oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	100	<1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		45		
	Calcium	ppm	ASTM D5185m		2191		
	Phosphorus	ppm	ASTM D5185m		953		
	Zinc	ppm	ASTM D5185m		1209		
	Sulfur	ppm	ASTM D5185m		3342		
	Oxidation	Abs/.1mm	*ASTM D7414		16.7		
	Base Number (BN)		ASTM D2896		7.6		
	Visc @ 100°C	cSt	ASTM D445	14.4	14.2		





Laboratory Sample No.

Lab Number : 06216497

: CU0023375 Unique Number : 11089361

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

Diagnosed Test Package: MOB 1 (Additional Tests: Glycol, TBN)

: 20 Jun 2024 : 23 Jun 2024

: 23 Jun 2024 - Don Baldridge

POINTE CLAIRE, QC CA H9R 1C2 Contact: Guy Emond guy.emond@cummins.com T: (514)695-8410

7200 TRANS CANADA HWY.

CUMMINS CANADA ULC

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (514)695-5246