WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL ATTENTION


Area

[25899]

VOLVO L70H 624698



VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Number	OOW	Client Info	LITTIOTOTT	VCP453719		
	Sample Date		Client Info		14 Jun 2024	12 Apr 2023	
	Machine Age	hrs	Client Info		1014	593	
	Oil Age	hrs	Client Info		0	500	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		Changed	Changed	
	Sample Status				ATTENTION	NORMAL	
WEAD	Iron	nnm	ASTM D5185m	> 200	24	32	
WEAR	Chromium	ppm	ASTM D5185m		24	2	
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1	0	
	Titanium	ppm	ASTM D5185m	>0			
	Silver	ppm	ASTM D5165III	. 2	<1 0	<1 0	
	Aluminum	ppm	ASTM D5185m		11	20	
	Lead	ppm	ASTM D5185m		<1	<1	
	Copper	ppm	ASTM D5185m		3	9	
	Tin		ASTM D5185m		ა 1	3	
	Vanadium	ppm	ASTM D5185m	/20	0	0	
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
			Visuai	INOINE			
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	14	19	
Fuel content negligible. No other contaminants were detected in the oil.	Potassium	ppm	ASTM D5185m	>20	2	3	
	Fuel	%	ASTM D3524	>6.0	2.1	<1.0	
	Water		WC Method	>0.2	NEG	NEG	
	Glycol		WC Method		NEG	NEG	
	Soot %	%	*ASTM D7844	>3	0.3	0.2	
	Nitration	Abs/cm	*ASTM D7624	>20	6.3	6.6	
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.4	19.5	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1	2	
	Boron	ppm	ASTM D5185m	2.5	63	45	
The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.	Barium	ppm	ASTM D5185m	0.0	0	0	
	Molybdenum	ppm	ASTM D5185m	0.7	25	38	
	Manganese	ppm	ASTM D5185m	0.0	2	5	
	Magnesium	ppm	ASTM D5185m	256	344	584	
	Calcium	ppm	ASTM D5185m	2057	2356	1536	
	Phosphorus	ppm	ASTM D5185m	935	962	961	
	Zinc	ppm	ASTM D5185m	1223	1213	1143	
	Sulfur	ppm	ASTM D5185m	4079	4865	3696	
	Oxidation	Abs/.1mm	*ASTM D7414		14.3	17.7	
	Base Number (BN)				10.3	8.9	
	Visc @ 100°C	cSt	ASTM D445	15.0	11.0	12.6	





Laboratory Sample No.

Lab Number : 06216538

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : VCP453719

Unique Number : 11089402

Received : 21 Jun 2024 **Tested** : 25 Jun 2024 Diagnosed

: 25 Jun 2024 - Sean Felton Test Package: MOB 1 (Additional Tests: FuelDilution, PercentFuel, TBN)

218 - ASCENDUM MACHINERY INC - N. CHARLESTON 7235 CROSS COUNTRY RD. NORTH CHARLESTON, SC

US 29418 Contact: MATT MITCHAM matt.mitcham@ascendummachinery.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (843)414-1129

Contact/Location: MATT MITCHAM - VOLVO3387

T: