



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
(TB7412) {UNASSIGNED}
Machine Id
7983
Component
Natural Gas Engine
Fluid
PETRO CANADA DURON GEO LD 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0123777	GFL0123763	GFL0113003
Sample Date		Client Info		14 Jun 2024	16 May 2024	11 Mar 2024
Machine Age	hrs	Client Info		2793	2761	2322
Oil Age	hrs	Client Info		32	2322	2322
Filter Age	hrs	Client Info		0	2761	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	5	13	18
Chromium	ppm	ASTM D5185m	>4	0	2	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	1	0
Aluminum	ppm	ASTM D5185m	>9	1	2	<1
Lead	ppm	ASTM D5185m	>30	0	<1	0
Copper	ppm	ASTM D5185m	>35	0	1	0
Tin	ppm	ASTM D5185m	>4	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	5	5	3
Potassium	ppm	ASTM D5185m	>20	3	3	0
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0	0
Nitration	Abs/cm	*ASTM D7624	>20	6.4	9.8	12.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.8	20.3	21.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		6	7	7
Boron	ppm	ASTM D5185m	50	43	21	13
Barium	ppm	ASTM D5185m	5	0	<1	0
Molybdenum	ppm	ASTM D5185m	50	48	56	60
Manganese	ppm	ASTM D5185m	0	<1	<1	0
Magnesium	ppm	ASTM D5185m	560	565	575	629
Calcium	ppm	ASTM D5185m	1510	1565	1682	2008
Phosphorus	ppm	ASTM D5185m	780	808	780	838
Zinc	ppm	ASTM D5185m	870	945	1006	1155
Sulfur	ppm	ASTM D5185m	2040	2826	2576	3131
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.5	17.3	18.8
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	8.4	6.4	5.3
Visc @ 100°C	cSt	ASTM D445	15.1	14.4	14.8	15.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0123777
Lab Number : 06216697
Unique Number : 11089561
Test Package : FLEET

Received : 21 Jun 2024
Tested : 24 Jun 2024
Diagnosed : 24 Jun 2024 - Wes Davis

GFL Environmental - 918 - Hartland HC
 630 E Industrial Drive
 Hartland, WI
 US 53029

Contact: David McCall
 david.mccall@gflenv.com
 T: (262)369-3069

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: