



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

(P633829)

Machine Id

3760C

Component

Natural Gas Engine

Fluid

PETRO CANADA DURON GEO LD 15W40 (40 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0125700	GFL0117985	GFL0101765
Sample Date		Client Info		20 Jun 2024	22 May 2024	09 Apr 2024
Machine Age	hrs	Client Info		17000	16714	16117
Oil Age	hrs	Client Info		600	597	600
Filter Age	hrs	Client Info		600	597	600
Oil Changed		Client Info		Not Changed	Changed	Changed
Filter Changed		Client Info		Not Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	11	9	13
Chromium	ppm	ASTM D5185m	>4	1	<1	2
Nickel	ppm	ASTM D5185m	>2	0	<1	<1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	<1	0
Aluminum	ppm	ASTM D5185m	>9	3	2	2
Lead	ppm	ASTM D5185m	>30	0	<1	1
Copper	ppm	ASTM D5185m	>35	1	1	<1
Tin	ppm	ASTM D5185m	>4	<1	<1	1
Vanadium	ppm	ASTM D5185m		0	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>+100	4	5	5
Potassium	ppm	ASTM D5185m	>20	5	3	2
Water		WC Method	>0.1	NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0.2	0
Nitration	Abs/cm	*ASTM D7624	>20	10.4	7.7	11.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	21.6	19.3	22.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		8	3	6
Boron	ppm	ASTM D5185m	50	10	3	8
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	50	51	59	56
Manganese	ppm	ASTM D5185m	0	<1	0	1
Magnesium	ppm	ASTM D5185m	560	570	952	566
Calcium	ppm	ASTM D5185m	1510	1695	1066	1666
Phosphorus	ppm	ASTM D5185m	780	777	991	679
Zinc	ppm	ASTM D5185m	870	1021	1246	983
Sulfur	ppm	ASTM D5185m	2040	2803	3197	2577
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.4	15.8	18.4
Base Number (BN)	mg KOH/g	ASTM D2896	10.2	4.7	7.2	3.9
Visc @ 100°C	cSt	ASTM D445	15.1	14.9	13.3	14.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0125700
Lab Number : 06216708
Unique Number : 11089572
Test Package : FLEET

Received : 21 Jun 2024
Tested : 24 Jun 2024
Diagnosed : 24 Jun 2024 - Wes Davis

GFL Environmental - 030 - Conway Myrtle Beach
 3010 HWY 378
 Conway, SC
 US 29527

Contact: ARCILIO RUEZ
 aruiz@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: