WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL

Machine Id

27070 Component Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		WC0939000		
	Sample Date		Client Info		11 Jun 2024		
	Machine Age	mls	Client Info		155526		
	Oil Age	mls	Client Info		155526		
	Filter Age	mls	Client Info		155526		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	nnm	ASTM D5185m	× 100	18		
	Chromium	ppm	ASTM D5185m		0		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m	74	0		
	Silver	ppm	ASTM D5185m	~3	<1		
	Aluminum	ppm	ASTM D5185m		7		
	Lead	ppm	ASTM D5185m		, <1		
	Copper	ppm	ASTM D5185m		8		
	Tin	ppm	ASTM D5185m		1		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	8		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	10		
	Fuel		WC Method		<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844		0.4		
	Nitration	Abs/cm	*ASTM D7624	>20	11.9		
	Sulfation	Abs/.1mm	*ASTM D7415		28.6		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Sodium	ppm	ASTM D5185m	>158	2		
	Boron	ppm	ASTM D5185m		39		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	100	108		
	Manganese	ppm	ASTM D5185m		1		
	Magnesium	ppm	ASTM D5185m	450	697		
	Calcium	ppm	ASTM D5185m		1652		
	Phosphorus	ppm	ASTM D5185m	1150	739		
	Zinc	ppm	ASTM D5185m	1350	912		
	Sulfur	ppm	ASTM D5185m	4250	3350		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	26.7		
	Base Number (BN)	mg KOH/g	ASTM D2896	8.5	4.7		
	Visc @ 100°C	cSt	ASTM D445	1///	12.9		







Certificate L2367

Laboratory Sample No.

: WC0939000 Lab Number : 06217613 Unique Number : 11090477 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 21 Jun 2024 **Tested** : 25 Jun 2024

Diagnosed : 25 Jun 2024 - Don Baldridge

SALEM NATIONALEASE CORPORATION

198 PARK PLAZA DRIVE WINSTON SALEM, NC US 27105

Contact: Audrey Hopkins

Audrey.Hopkins@salemcorp.com T: (336)767-9642

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: