



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
162109
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		IL06217717	IL06055295	IL05254821
Sample Date		Client Info		09 May 2024	08 Dec 2023	22 Apr 2021
Machine Age	hrs	Client Info		12820	11265	2667
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	9	14	94
Chromium	ppm	ASTM D5185m	>20	<1	1	4
Nickel	ppm	ASTM D5185m	>4	0	<1	1
Titanium	ppm	ASTM D5185m		0	<1	<1
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	2	2	29
Lead	ppm	ASTM D5185m	>40	0	<1	12
Copper	ppm	ASTM D5185m	>330	<1	2	73
Tin	ppm	ASTM D5185m	>15	0	<1	2
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	8	7	10
Potassium	ppm	ASTM D5185m	>20	1	5	▲ 85
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1	1.4	▲ 4.7
Nitration	Abs/cm	*ASTM D7624	>20	8.2	8.8	17.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.5	21.2	36.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>216	1	0	5
Boron	ppm	ASTM D5185m	250	2	7	19
Barium	ppm	ASTM D5185m	10	0	0	<1
Molybdenum	ppm	ASTM D5185m	100	63	65	64
Manganese	ppm	ASTM D5185m		<1	<1	4
Magnesium	ppm	ASTM D5185m	450	1033	888	499
Calcium	ppm	ASTM D5185m	3000	1251	1090	1813
Phosphorus	ppm	ASTM D5185m	1150	1104	864	995
Zinc	ppm	ASTM D5185m	1350	1379	1161	1218
Sulfur	ppm	ASTM D5185m	4250	3863	3424	2379
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.8	14.8	29.8
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	9.5	8.4	4.2
Visc @ 100°C	cSt	ASTM D445	14.4	13.7	13.4	14.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : IL06217717
Lab Number : 06217717
Unique Number : 11090581
Test Package : FLEET

Received : 24 Jun 2024
Tested : 25 Jun 2024
Diagnosed : 25 Jun 2024 - Wes Davis

RUSH TRUCK LEASING - CINCINNATI IDEALEASE
 11777 HIGHWAY DRIVE
 CINCINNATI, OH
 US 45241

Contact: ROBERT BAIER
 baierr@rushenterprises.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (513)657-7901
 F: (513)733-0537