WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Machine Id

8927817

Component
Diesel Engine

{not provided} (--- QTS)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
TECOMINIENDATION	Sample Number	JOIVI	Client Info	LIIIIUAUII	IL06217763		
Resample at the next service interval to monitor.	Sample Date		Client Info		23 Jun 2024		
	Machine Age	mls	Client Info		0		
	Oil Age	mls	Client Info		0		
	Filter Age	mls	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	20		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m		5		
	Lead	ppm	ASTM D5185m		1		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m	>15	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	22		
CONTAMINATION	Potassium	ppm	ASTM D5185m		9		
There is no indication of any contamination in the oil.	Fuel	%	ASTM D3524		<1.0		
	Water	, , ,	WC Method		NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.4		
	Nitration	Abs/cm	*ASTM D7624	>20	10.3		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	24.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		2		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		28		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		48		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		520		
	Calcium	ppm	ASTM D5185m		1800		
	Phosphorus	ppm	ASTM D5185m		809		
	Zinc	ppm	ASTM D5185m		964		
	Sulfur	ppm	ASTM D5185m		2772		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	24.6		
	Base Number (BN)	mg KOH/g	ASTM D2896		7.9		
	Visc @ 100°C	cSt	ASTM D445		11.0		







Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : IL06217763 Lab Number : 06217763

Unique Number : 11090627

Received **Tested** Diagnosed

: 25 Jun 2024 : 25 Jun 2024 - Don Baldridge Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel)

: 24 Jun 2024

IDEALEASE-NORCROSS 4571 NORTH BUFORD HWY NORCROSS, GA US 30071-2808 Contact: RICK MARKS

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)