



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
CLI TRANSPORT LP - MANASSAS
 Machine Id
VOLVO 8590 (S/N 4V4NC9EH4NN604102)
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		NL0002240	NL0001841	NL0001692
Sample Date		Client Info		08 May 2024	29 Jan 2024	23 Oct 2023
Machine Age	mls	Client Info		360436	324043	285905
Oil Age	mls	Client Info		45000	45000	45000
Filter Age	mls	Client Info		45000	45000	45000
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	70	73	36
Chromium	ppm	ASTM D5185m	>20	1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>2	<1	0	<1
Aluminum	ppm	ASTM D5185m	>25	5	5	3
Lead	ppm	ASTM D5185m	>40	4	2	1
Copper	ppm	ASTM D5185m	>330	12	14	6
Tin	ppm	ASTM D5185m	>15	2	1	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	8	8	8
Potassium	ppm	ASTM D5185m	>20	4	5	5
Fuel		WC Method	>6.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.6	0.6	0.3
Nitration	Abs/cm	*ASTM D7624	>20	10.6	10.4	7.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.4	23.4	19.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	0	0
Boron	ppm	ASTM D5185m	0	12	2	3
Barium	ppm	ASTM D5185m	0	2	<1	4
Molybdenum	ppm	ASTM D5185m	60	69	61	65
Manganese	ppm	ASTM D5185m	0	1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	899	876	924
Calcium	ppm	ASTM D5185m	1070	1189	1118	1129
Phosphorus	ppm	ASTM D5185m	1150	996	948	1092
Zinc	ppm	ASTM D5185m	1270	1272	1164	1240
Sulfur	ppm	ASTM D5185m	2060	2906	2892	3375
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.4	19.5	15.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	5.3	5.4	8.6
Visc @ 100°C	cSt	ASTM D445	15.4	13.8	13.8	14.0


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Viscosity @ 100°C




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : NL0002240
Lab Number : 06217838
Unique Number : 11096035
Test Package : FLEET

Received : 24 Jun 2024
Tested : 25 Jun 2024
Diagnosed : 25 Jun 2024 - Wes Davis

FOX & JAMES NATIONALEASE - Manassas
 1145 INDUSTRIAL RD
 MANASSAS, VA
 US 20109
 Contact: JOSH ROLAND
 j.roland@foxandjames.com
 T: (571)379-5296
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)