



VOLVO

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
[590794 ASH GROVE]
 Machine Id
VOLVO A40G 352940
 Component
Hydraulic System
 Fluid
VOLVO SUPER HYDRAULIC OIL 46 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP447367	VCP440294	VCP411709
Sample Date		Client Info		19 Jun 2024	26 Sep 2023	30 May 2023
Machine Age	hrs	Client Info		9064	6962	5463
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Filter Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	6	5	6
Chromium	ppm	ASTM D5185m	>20	0	0	<1
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	<1	0
Lead	ppm	ASTM D5185m	>20	2	1	1
Copper	ppm	ASTM D5185m	>150	2	1	2
Tin	ppm	ASTM D5185m	>20	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	▲ MODER	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>20	5	4	7
Potassium	ppm	ASTM D5185m	>20	2	0	1
Water		WC Method	>0.1	NEG	NEG	NEG
Particles >4µm		ASTM D7647		12270	---	1370
Particles >6µm		ASTM D7647	>5000	3843	---	193
Particles >14µm		ASTM D7647	>160	154	---	14
Particles >21µm		ASTM D7647	>40	17	---	3
Particles >38µm		ASTM D7647	>10	1	---	0
Particles >71µm		ASTM D7647	>3	0	---	0
Oil Cleanliness		ISO 4406 (c)	>-/19/14	21/19/14	---	18/15/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	<1	0
Boron	ppm	ASTM D5185m	14	2	0	0
Barium	ppm	ASTM D5185m	0.0	0	0	0
Molybdenum	ppm	ASTM D5185m	0.0	<1	1	2
Manganese	ppm	ASTM D5185m	0.0	<1	0	0
Magnesium	ppm	ASTM D5185m	2.6	11	12	12
Calcium	ppm	ASTM D5185m	49	599	610	1103
Phosphorus	ppm	ASTM D5185m	354	475	454	522
Zinc	ppm	ASTM D5185m	419	587	545	680
Sulfur	ppm	ASTM D5185m	3719	3479	2864	3454
Acid Number (AN)	mg KOH/g	ASTM D8045		0.53	0.54	0.73
Visc @ 40°C	cSt	ASTM D445	46	48.0	50.0	53.0



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VCP447367
Lab Number : 06218096
Unique Number : 11096293
Test Package : MOB 2

ALTA EQUIPMENT/FLAGLER EQUIPMENT LLC
 9601 BOGGY CREEK RD
 ORLANDO, FL
 US 32824
 Contact: Robert LaPlante
 robert.laplante@altg.com
 T: (407)508-9736
 F: (407)659-8720

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)