**OIL ANALYSIS REPORT** 

**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

## **CATERPILLAR 552 FELLER 16-04 (S/N CAT00552PFG00199)**

Swing Drive

Machine Id

CAT TOTO SAF 50 (--- GAL)

| CAT TDTO SAE 50 ( GAL)   |                      |          |             |           | .,          |          |          |
|--|----------------------|----------|-------------|-----------|-------------|----------|----------|
| RECOMMENDATION   | Test                 | UOM      | Method      | Limit/Abn | Current     | History1 | History2 |
| Resample at the next service interval to monitor.  | Sample Number        |          | Client Info |           | TR06218408  |          |          |
|  | Sample Date          |          | Client Info |           | 08 May 2024 |          |          |
|  | Machine Age          | hrs      | Client Info |           | 6486        |          |          |
|  | Oil Age              | hrs      | Client Info |           | 1607        |          |          |
|  | Filter Age           | hrs      | Client Info |           | 0           |          |          |
|  | Oil Changed          |          | Client Info |           | Changed     |          |          |
|  | Filter Changed       |          | Client Info |           | N/A         |          |          |
|  | Sample Status        |          |             |           | NORMAL      |          |          |
| WEAR   | Iron                 | ppm      | ASTM D5185m | >400      | 51          |          |          |
|  | Chromium             | ppm      | ASTM D5185m | >10       | <1          |          |          |
| All component wear rates are normal.   | Nickel               | ppm      | ASTM D5185m |           | <1          |          |          |
|  | Titanium             | ppm      | ASTM D5185m |           | <1          |          |          |
|  | Silver               | ppm      | ASTM D5185m |           | <1          |          |          |
|  | Aluminum             | ppm      | ASTM D5185m | >25       | 2           |          |          |
|  | Lead                 | ppm      | ASTM D5185m |           | 2           |          |          |
|  | Copper               | ppm      | ASTM D5185m | >200      | 3           |          |          |
|  | Tin                  | ppm      | ASTM D5185m |           | <1          |          |          |
|  | Vanadium             | ppm      | ASTM D5185m |           | <1          |          |          |
|  | White Metal          | scalar   | *Visual     | NONE      | NONE        |          |          |
|  | Yellow Metal         | scalar   | *Visual     | NONE      | NONE        |          |          |
|  |                      |          |             |           |             |          |          |
| CONTAMINATION  | Silicon              | ppm      | ASTM D5185m |           | 9           |          |          |
| There is no indication of any contamination in the oil.  | Potassium            | ppm      | ASTM D5185m |           | 3           |          |          |
|  | Water                |          | WC Method   | >0.2      | NEG         |          |          |
|  | Silt                 | scalar   | *Visual     | NONE      | MODER       |          |          |
|  | Debris               | scalar   | *Visual     | NONE      | NONE        |          |          |
|  | Sand/Dirt            | scalar   | *Visual     | NONE      | NONE        |          |          |
|  | Appearance           | scalar   | *Visual     | NORML     | NORML       |          |          |
|  | Odor                 | scalar   | *Visual     | NORML     | NORML       |          |          |
|  | Emulsified Water     | scalar   | *Visual     | >0.2      | NEG         |          |          |
| FLUID CONDITION  | Sodium               | ppm      | ASTM D5185m |           | 3           |          |          |
| The AN level is acceptable for this fluid. The condition of the oil is suitable for further service. | Boron                | ppm      | ASTM D5185m |           | 11          |          |          |
|  | Barium               | ppm      | ASTM D5185m |           | 0           |          |          |
|  | Molybdenum           | ppm      | ASTM D5185m |           | <1          |          |          |
|  | Manganese            | ppm      | ASTM D5185m |           | 1           |          |          |
|  | Magnesium            | ppm      | ASTM D5185m | 0000      | 10          |          |          |
|  | Calcium              | ppm      | ASTM D5185m |           | 3010        |          |          |
|  | Phosphorus           | ppm      | ASTM D5185m |           | 1091        |          |          |
|  | Zinc                 | ppm      | ASTM D5185m | 12/0      | 1247        |          |          |
|  | Sulfur               | ppm      | ASTM D5185m |           | 12123       |          |          |
|  | Acid Number (AN)     | mg KOH/g |             | 105       | 1.58        |          |          |
|  | Visc @ 40°C          | cSt      | ASTM D445   |           | 196         |          |          |
|  | Visc @ 100°C         | cSt      | ASTM D445   |           | 17.2        |          |          |
|  | Viscosity Index (VI) | Scale    | ASTM D2270  | 96        | 93          |          |          |





Laboratory Sample No. Unique Number : 11096605

Lab Number : 06218408

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : TR06218408 **Tested** 

Diagnosed Test Package : MOB 2 (Additional Tests: KV100, VI)

: 24 Jun 2024 : 25 Jun 2024

: 25 Jun 2024 - Wes Davis

**KASKI LOGGING** 22411 HE CEDAR CREEK RD AMBOY, WA

US 98601 Contact: NATHAN BYRD

To discuss this sample report, contact Customer Service at 1-800-827-0711.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: