



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
WCLSNC
 Machine Id
QC230801DE
 Component
Diesel Engine
 Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0952365	WC0952362	WC0952361
Sample Date		Client Info		24 Jun 2024	21 Jun 2024	20 Jun 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>11	9	6	10
Chromium	ppm	ASTM D5185m	>3	1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m	>2	<1	0	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>5	3	2	2
Lead	ppm	ASTM D5185m	>2	2	0	0
Copper	ppm	ASTM D5185m	>7	4	4	4
Tin	ppm	ASTM D5185m	>2	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>14	5	8	4
Potassium	ppm	ASTM D5185m	>20	5	3	<1
Fuel	%	ASTM D3524	>4.1	2.3	2.2	2.2
Water	%	ASTM D6304	>0.2	NEG	NEG	NEG
Glycol	%	*ASTM D2982		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>0.3	0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>10.8	10.4	10.6	10.4
Sulfation	Abs/.1mm	*ASTM D7415	>20.8	19.8	20.2	19.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>13	8	8	7
Boron	ppm	ASTM D5185m	0	6	7	10
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	50	54	49
Manganese	ppm	ASTM D5185m	0	<1	0	<1
Magnesium	ppm	ASTM D5185m	1010	553	527	522
Calcium	ppm	ASTM D5185m	1070	1671	1498	1522
Phosphorus	ppm	ASTM D5185m	1150	739	691	687
Zinc	ppm	ASTM D5185m	1270	991	947	922
Sulfur	ppm	ASTM D5185m	2060	2937	2295	2782
Oxidation	Abs/.1mm	*ASTM D7414	>17.9	17.0	17.3	17.1
Acid Number (AN)	mg KOH/g	ASTM D8045	3.2	0.89	0.86	0.85
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.63	7.12	6.99
Visc @ 40°C	cSt	ASTM D445	113.9	97.52	97.93	97.8
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	13.4	13.4
Viscosity Index (VI)	Scale	ASTM D2270	142	136	136	136



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0952365
Lab Number : 06218414
Unique Number : 11096611
Test Package : MOB 2 (Additional Tests: FuelDilution, Glycol, KF, KV40, PercentFuel, VI)

Received : 24 Jun 2024
Tested : 27 Jun 2024
Diagnosed : 27 Jun 2024 - Jonathan Hester

WEARCHECK LUBRICATION SERVICES QA ACCOUNT
 501 Madison Ave
 Cary, NC
 US 27513
 Contact: WCLS CARY NC

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (919)379-4102
 F: (919)379-4050