

[G15429] JOHN DEERE 350G 812159 Component Left Final Drive

JOHN DEERE GL-5 80W90 (--- GAL)

RECOMMENDATION

We advise that you check all areas where dirt can enter the system. Oil and filter change at the time of sampling has been noted. We advise that you inspect for the source(s) of wear. We recommend an early resample to monitor this condition.

WEAR

Gear wear is indicated.

CONTAMINATION

Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress. There is a light concentration of water present in the oil.

UOM Method Limit/Abn Current History1

CONTAMINATION

FLUID CONDITION

WEAR

SEVERE

SEVERE


NORMAL

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WE0007097		
Sample Date		Client Info		18 Jun 2024		
Machine Age	hrs	Client Info		3115		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		Changed		
Sample Status				SEVERE		
PQ		ASTM D8184	>1250	282		
Iron	ppm	ASTM D5185m	>750	A 2097		
Chromium	ppm	ASTM D5185m	>9	A 22		
Nickel	ppm	ASTM D5185m	>10	5		
Titanium	ppm	ASTM D5185m		5		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>40	4 4		
Lead	ppm	ASTM D5185m	>15	<1		
Copper	ppm	ASTM D5185m	>40	5		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>75	4 12		
Potassium	ppm	ASTM D5185m	>20	10		
Water	%	ASTM D6304	>0.075	▲ 0.217		
ppm Water	ppm	ASTM D6304	>750	2170		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.075	<mark>▲</mark> 0.2%		
Sodium	ppm	ASTM D5185m	>51	1		
Boron	ppm	ASTM D5185m		18		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		2		
Manganese	ppm	ASTM D5185m		20		
Magnesium	ppm	ASTM D5185m		10		
Calcium	ppm	ASTM D5185m		113		
Phosphorus	ppm	ASTM D5185m		317		
Zinc	ppm	ASTM D5185m		24		
Sulfur	ppm	ASTM D5185m		17388		
Visc @ 40°C	cSt	ASTM D445		204	 DVDVCT M	

FLUID CONDITION

The oil is no longer serviceable due to the presence of contaminants.

Contact/Location: BEN BYRKET - WARGRAAL



WARRIOR TRACTOR AND EQUIPMENT - GRAYSVILLE Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : WE0007097 Received : 24 Jun 2024 4308 WATER TRAIL Ŭ Lab Number : 06218481 Tested GRAYSVILLE, AL : 25 Jun 2024 : 25 Jun 2024 - Sean Felton US 35073 Unique Number : 11096678 Diagnosed Test Package : CONST (Additional Tests: KF, PQ) Contact: BEN BYRKET Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. bbyrket@warriortractor.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (205)675-9045 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

Contact/Location: BEN BYRKET - WARGRAAL Page 2 of 2