

WEAR SEVERE CONTAMINATION SEVERE FLUID CONDITION NORMAL



Store 4 - Fairmont [RO# 152218] JOHN DEERE 325G 1T0325GMJKJ349749 Right Drive Chain Case

JOHN DEERE GL-5 80W90 (27 Oz)

RECOMMENDATION

.....

We advise that you check all areas where dirt can enter the system. The oil change at the time of sampling has been noted. We advise that you inspect for the source(s) of wear. We recommend an early resample to monitor this condition.

WEAR

Gear wear is indicated.

CONTAMINATION


Elemental levels of silicon (Si) and aluminum (AI) indicate aluminasilicate (coarse dirt) ingress.

FLUID CONDITION

The oil is no longer serviceable due to the presence of contaminants.

<i>32</i>)						
Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0051057		
Sample Date		Client Info		19 Jun 2024		
Machine Age	hrs	Client Info		2368		
Oil Age	hrs	Client Info		1000		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		N/A		
Sample Status				SEVERE		
DO						
PQ		ASTM D8184	000	97		
Iron	ppm	ASTM D5185m	>200	▲ 2270 ▲ 07		
Chromium	ppm	ASTM D5185m	>10	▲ 27 ▲ 22		
Nickel	ppm	ASTM D5185m	>10	▲ 20 C		
Titanium	ppm	ASTM D5185m		6		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m		61		
Lead	ppm	ASTM D5185m		1		
Copper	ppm	ASTM D5185m		5		
Tin	ppm	ASTM D5185m		0		
Vanadium	ppm	ASTM D5185m		2		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m		382		
Potassium	ppm	ASTM D5185m	>20	30		
Water	1-1-	WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium	ppm	ASTM D5185m		8		
Boron	ppm	ASTM D5185m		29		
Barium	ppm	ASTM D5185m		5		
Molybdenum	ppm	ASTM D5185m		8		
Manganese	ppm	ASTM D5185m		19		
Magnesium	ppm	ASTM D5185m		82		
Calcium	ppm	ASTM D5185m		2779		
Phosphorus	ppm	ASTM D5185m		832		
Zinc	ppm	ASTM D5185m		927		
Sulfur	ppm	ASTM D5185m		3641		
Visc @ 40°C	cSt	ASTM D445		88.2		

Submitted By: APRIL TREADWAY



LESLIE EQUIPMENT COMPANY Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. Received : 24 Jun 2024 105 TENNIS CENTER DR. : LEC0051057 Lab Number : 06218544 Tested MARIETTA, OH : 25 Jun 2024 Unique Number : 11096741 Diagnosed : 26 Jun 2024 - Sean Felton US 45750-9765 Test Package : CONST (Additional Tests: PQ) Contact: LEANNE KENDALL Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. KendalLeanne@lec1.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (740)373-5570

Submitted By: APRIL TREADWAY Page 2 of 2