

## Machine Id

## JOHN DEERE 350P 1FF350PAJRF001350

Left Final Drive

## JOHN DEERE GL-5 80W90 (--- QTS)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0218189		
	Sample Date		Client Info		15 Jun 2024		
	Machine Age	hrs	Client Info		531		
	Oil Age	hrs	Client Info		531		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>1250	100		
	Iron	ppm	ASTM D5185m		164		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		3		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>40	3		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		1		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		15		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	0		
	Boron	ppm	ASTM D5185m		77		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		3		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m		<1		
	Calcium	ppm	ASTM D5185m		16		
	Phosphorus	ppm	ASTM D5185m		506		
	Zinc	ppm	ASTM D5185m		15		

Sulfur Visc @ 40°C

Submitted By: TECHNICIAN ACCOUNT


14583


187


ppm ASTM D5185m

cSt

ASTM D445







Submitted By: TECHNICIAN ACCOUNT Page 2 of 2