WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

[591916 NAT FLEET] VOLVO A45G 353508 Component Bogie/Center Axle

Bogie/Center Axle [Fluid] {not provided} (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		VCP444748		
	Sample Date		Client Info		20 Jun 2024		
	Machine Age	hrs	Client Info		1680		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>900	433		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	6		
	Nickel	ppm	ASTM D5185m		2		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>30	3		
	Lead	ppm	ASTM D5185m	>50	<1		
	Copper	ppm	ASTM D5185m	>150	6		
	Tin	ppm	ASTM D5185m	>20	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	6		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	5		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	MODER		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		214		
	Barium	ppm	ASTM D5185m		1		
	Molybdenum	ppm	ASTM D5185m		4		
	Manganese	ppm	ASTM D5185m		12		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		120		
	Phosphorus	ppm	ASTM D5185m		2321		
	Zinc	ppm	ASTM D5185m		57		

Sulfur

Visc @ 40°C


25592

52.2

ASTM D5185m

ASTM D445

ppm





Certificate L2367

Laboratory Sample No.

: VCP444748 Lab Number : 06218589 Unique Number : 11096786 Test Package : MOB 1

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 24 Jun 2024 **Tested**

: 25 Jun 2024 : 26 Jun 2024 - Sean Felton Diagnosed

8418 PALM RIVER ROAD

ALTA EQUIPMENT/FLAGLER CONSTRUCTION EQUIPMENT LLC

TAMPA, FL US 33619

T: (813)630-0077

F: (813)630-2233

Contact: KENNY HANEY khaney@flaglerce.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.