



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
1707
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0897858	WC0897904	WC0894022
Sample Date		Client Info		05 Jun 2024	06 May 2024	15 Mar 2024
Machine Age	mls	Client Info		0	0	0
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	N/A
Filter Changed		Client Info		Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	12	17	14
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	1	2	2
Lead	ppm	ASTM D5185m	>40	0	<1	0
Copper	ppm	ASTM D5185m	>330	11	77	37
Tin	ppm	ASTM D5185m	>15	0	<1	0
Vanadium	ppm	ASTM D5185m		<1	<1	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	10	17	▲ 26
Potassium	ppm	ASTM D5185m	>20	2	3	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.3	0.1
Nitration	Abs/cm	*ASTM D7624	>20	8.2	8.9	8.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.6	23.6	21.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>158	2	1	4
Boron	ppm	ASTM D5185m	250	<1	0	43
Barium	ppm	ASTM D5185m	10	0	2	5
Molybdenum	ppm	ASTM D5185m	100	58	59	50
Manganese	ppm	ASTM D5185m		<1	<1	7
Magnesium	ppm	ASTM D5185m	450	974	878	813
Calcium	ppm	ASTM D5185m	3000	1134	1082	1237
Phosphorus	ppm	ASTM D5185m	1150	1025	997	776
Zinc	ppm	ASTM D5185m	1350	1299	1182	934
Sulfur	ppm	ASTM D5185m	4250	3454	2702	2895
Oxidation	Abs/.1mm	*ASTM D7414	>25	22.4	25.4	21.3
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	7.3	6.5	8.3
Visc @ 100°C	cSt	ASTM D445	14.4	13.7	13.5	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0897858 **Received** : 24 Jun 2024
Lab Number : 06219135 **Tested** : 25 Jun 2024
Unique Number : 11097332 **Diagnosed** : 25 Jun 2024 - Wes Davis
Test Package : MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

GO DURHAM - RATP
 1903 FAYETTEVILLE ST
 DURHAM, NC
 US 27701

Contact: Robert Iosiniecki
 Robert.iosiniecki@ratpdev.com

T:
 F: