



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
413115
Component
Diesel Engine
Fluid
PETRO CANADA DURON UHP 5W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0122899	GFL0122797	GFL0122941
Sample Date		Client Info		20 Jun 2024	13 Jun 2024	21 May 2024
Machine Age	hrs	Client Info		3210	3162	3024
Oil Age	hrs	Client Info		2927	2879	2888
Filter Age	hrs	Client Info		0	---	0
Oil Changed		Client Info		Changed	N/A	Not Changd
Filter Changed		Client Info		Changed	Not Changd	Not Changd
Sample Status				NORMAL	---	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	13	---	8
Chromium	ppm	ASTM D5185m	>20	<1	---	0
Nickel	ppm	ASTM D5185m	>15	1	---	2
Titanium	ppm	ASTM D5185m	>2	<1	---	0
Silver	ppm	ASTM D5185m	>3	0	---	<1
Aluminum	ppm	ASTM D5185m	>20	2	---	3
Lead	ppm	ASTM D5185m	>40	0	---	<1
Copper	ppm	ASTM D5185m	>330	4	---	2
Tin	ppm	ASTM D5185m	>15	0	---	<1
Vanadium	ppm	ASTM D5185m		<1	---	0
White Metal	scalar	*Visual	NONE	NONE	---	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	---	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	---	4
Potassium	ppm	ASTM D5185m	>20	4	---	3
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>4	0.4	---	0.2
Nitration	Abs/cm	*ASTM D7624	>20	9.9	---	8.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.8	---	19.7
Silt	scalar	*Visual	NONE	NONE	---	NONE
Debris	scalar	*Visual	NONE	NONE	---	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	---	NONE
Appearance	scalar	*Visual	NORML	NORML	---	NORML
Odor	scalar	*Visual	NORML	NORML	---	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	---	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		4	---	4
Boron	ppm	ASTM D5185m	0	19	---	32
Barium	ppm	ASTM D5185m	0	0	---	0
Molybdenum	ppm	ASTM D5185m	64	58	---	57
Manganese	ppm	ASTM D5185m	0	<1	---	<1
Magnesium	ppm	ASTM D5185m	1160	1160	---	1165
Calcium	ppm	ASTM D5185m	820	893	---	840
Phosphorus	ppm	ASTM D5185m	1160	1056	---	1031
Zinc	ppm	ASTM D5185m	1260	1333	---	1315
Sulfur	ppm	ASTM D5185m	3000	3865	---	3855
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.8	---	17.5
Base Number (BN)	mg KOH/g	ASTM D2896	11.0	7.9	---	8.4
Visc @ 100°C	cSt	ASTM D445	11.9	11.7	---	11.7



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0122899
Lab Number : 06219158
Unique Number : 11097355
Test Package : FLEET

Received : 24 Jun 2024
Tested : 25 Jun 2024
Diagnosed : 25 Jun 2024 - Wes Davis

GFL Environmental - 836 - Kansas City Hauling
 7801 East Truman Road
 Kansas City, MO
 US 64126
 Contact: Loyce Stewart
 loyce.stewart@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: