



# WEAR CHECK

## OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**2334**  
 Component  
**Diesel Engine**  
 Fluid  
**ROYAL PURPLE MOTOR OIL 15W40 (--- QTS)**

### RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>WC0720013</b>	WC0719881	WC0719869
Sample Date		Client Info		<b>28 Apr 2024</b>	19 Feb 2024	16 Sep 2023
Machine Age	mls	Client Info		<b>267305</b>	242247	170762
Oil Age	mls	Client Info		<b>50000</b>	50000	50000
Filter Age	mls	Client Info		<b>50000</b>	50000	50000
Oil Changed		Client Info		<b>Not Changd</b>	Not Changd	Not Changd
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>40</b>	25	30
Chromium	ppm	ASTM D5185m	>20	<b>2</b>	<1	2
Nickel	ppm	ASTM D5185m	>4	<b>1</b>	<1	<1
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m	>3	<b>&lt;1</b>	0	0
Aluminum	ppm	ASTM D5185m	>20	<b>10</b>	8	15
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	<1	<1
Copper	ppm	ASTM D5185m	>330	<b>43</b>	34	86
Tin	ppm	ASTM D5185m	>15	<b>1</b>	0	<1
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

### CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	<b>8</b>	6	7
Potassium	ppm	ASTM D5185m	>20	<b>28</b>	18	33
Fuel		WC Method	>5	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>3	<b>0.9</b>	0.6	0.8
Nitration	Abs/cm	*ASTM D7624	>20	<b>9.9</b>	8.5	10.9
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>23.3</b>	20.4	22.8
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

### FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>0</b>	2	3
Boron	ppm	ASTM D5185m	0	<b>0</b>	0	0
Barium	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	0
Molybdenum	ppm	ASTM D5185m	100	<b>3</b>	2	10
Manganese	ppm	ASTM D5185m		<b>1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	60	<b>38</b>	43	155
Calcium	ppm	ASTM D5185m	3050	<b>2592</b>	2650	2189
Phosphorus	ppm	ASTM D5185m	1050	<b>1036</b>	1015	808
Zinc	ppm	ASTM D5185m	1200	<b>1157</b>	1162	1059
Sulfur	ppm	ASTM D5185m	12500	<b>3411</b>	3642	2551
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>16.8</b>	13.2	19.0
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	<b>5.1</b>	6.0	5.2
Visc @ 100°C	cSt	ASTM D445	14.9	<b>13.3</b>	12.9	13.1


**FT-IR (Direct Trend)**




**Ferrous Alloys**




**Base Number**




**Viscosity @ 100°C**




**Non-ferrous Metals**



**Viscosity @ 100°C**



**Base Number**



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0720013  
**Lab Number** : 06219213  
**Unique Number** : 11097410  
**Test Package** : FLEET

**Received** : 24 Jun 2024  
**Tested** : 25 Jun 2024  
**Diagnosed** : 25 Jun 2024 - Wes Davis

**DILLON TRANSPORTATION**  
 4445 NORTH INTERSTATE WAY  
 KINGMAN, AZ  
 US 86401  
 Contact: T LAMOREAUX  
 t.lamoreaux@dillontransportation.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: