



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
112387
Component
Diesel Engine
Fluid
SHELL ROTELLA T 15W40 (--- QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		IL0032946	IL0027500	IL0020046
Sample Date		Client Info		11 Jun 2024	24 Mar 2023	24 Jun 2022
Machine Age	mls	Client Info		194905	142519	103394
Oil Age	mls	Client Info		27880	46341	16750
Filter Age	mls	Client Info		27880	46341	16750
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	13	17	7
Chromium	ppm	ASTM D5185m	>20	1	2	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	<1
Aluminum	ppm	ASTM D5185m	>20	2	0	3
Lead	ppm	ASTM D5185m	>40	2	2	1
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	3	4
Potassium	ppm	ASTM D5185m	>20	5	3	4
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.3	0.5	0.1
Nitration	Abs/cm	*ASTM D7624	>20	10.4	11.9	9.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.0	26.3	21.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	2	2
Boron	ppm	ASTM D5185m	316	39	21	62
Barium	ppm	ASTM D5185m	0.0	0	11	0
Molybdenum	ppm	ASTM D5185m	1.2	37	50	62
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m	24	377	54	55
Calcium	ppm	ASTM D5185m	2292	1976	1505	2295
Phosphorus	ppm	ASTM D5185m	1064	1097	655	984
Zinc	ppm	ASTM D5185m	1160	1349	838	1227
Sulfur	ppm	ASTM D5185m	4996	3754	2615	4207
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.0	21.7	16.9
Base Number (BN)	mg KOH/g	ASTM D2896	10.1	5.7	5.2	6.2
Visc @ 100°C	cSt	ASTM D445	15.7	13.3	13.3	13.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : IL0032946

Lab Number : 06219355

Unique Number : 11097552

Test Package : FLEET

Received : 25 Jun 2024

Tested : 25 Jun 2024

Diagnosed : 25 Jun 2024 - Wes Davis

IDEALEASE OF NORTHWEST WI

611 HANSEN ROAD

GREEN BAY, WI

US 54304

Contact: GARY KOLTZ

gkoltz@pcitrucks.com

T: (920)499-6200

F: (920)499-5332

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)