



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
PETERBILT 14001
Component
Diesel Engine
Fluid
CHEVRON 15W40 (25 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0924451	WC0809954	WC0856876
Sample Date		Client Info		24 Jun 2024	21 Dec 2023	14 Oct 2023
Machine Age	hrs	Client Info		16826	16472	16222
Oil Age	hrs	Client Info		0	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	32	12	8
Chromium	ppm	ASTM D5185m	>20	1	<1	<1
Nickel	ppm	ASTM D5185m	>4	<1	0	<1
Titanium	ppm	ASTM D5185m		1	<1	2
Silver	ppm	ASTM D5185m	>3	<1	<1	<1
Aluminum	ppm	ASTM D5185m	>20	5	3	3
Lead	ppm	ASTM D5185m	>40	3	0	1
Copper	ppm	ASTM D5185m	>330	9	1	<1
Tin	ppm	ASTM D5185m	>15	2	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	11	6	5
Potassium	ppm	ASTM D5185m	>20	3	0	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1.8	0.8	0.7
Nitration	Abs/cm	*ASTM D7624	>20	9.3	6.8	6.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.1	21.1	19.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>50	<1	3	0
Boron	ppm	ASTM D5185m		300	352	350
Barium	ppm	ASTM D5185m		2	<1	0
Molybdenum	ppm	ASTM D5185m		86	87	84
Manganese	ppm	ASTM D5185m		1	<1	<1
Magnesium	ppm	ASTM D5185m		368	378	415
Calcium	ppm	ASTM D5185m		1335	1308	1416
Phosphorus	ppm	ASTM D5185m		867	1002	1157
Zinc	ppm	ASTM D5185m		1156	1185	1441
Sulfur	ppm	ASTM D5185m		2803	2971	3753
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.3	13.7	12.9
Base Number (BN)	mg KOH/g	ASTM D2896		7.6	7.2	6.8
Visc @ 100°C	cSt	ASTM D445	14.4	13.3	13.2	13.6



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0924451 **Received** : 25 Jun 2024
Lab Number : 06219512 **Tested** : 26 Jun 2024
Unique Number : 11097709 **Diagnosed** : 26 Jun 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

SULLIVAN EASTERN INC
 2860 C SLATER RD
 MORRISVILLE, NC
 US 27560
 Contact: SCOTT SULLIVAN
 ssullivan@sullivaneastern.com
 T: (919)484-8993
 F: (919)484-2136

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)