



ASCENDUM

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
VOLVO L180H 5557
Component
Diesel Engine
Fluid
VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		ASC0003172	VCP416388	VCP340452
Sample Date		Client Info		24 Jun 2024	08 Aug 2023	25 May 2022
Machine Age	hrs	Client Info		1993	1502	506
Oil Age	hrs	Client Info		491	0	0
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	7	7	12
Chromium	ppm	ASTM D5185m	>20	<1	0	<1
Nickel	ppm	ASTM D5185m	>5	1	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>30	3	1	3
Lead	ppm	ASTM D5185m	>40	1	<1	1
Copper	ppm	ASTM D5185m	>20	9	13	286
Tin	ppm	ASTM D5185m	>20	1	2	3
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	6	6	23
Potassium	ppm	ASTM D5185m	>20	5	<1	4
Fuel		WC Method	>6.0	<1.0	<1.0	0.6
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	7.7	7.3	9.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.3	22.0	18.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	2	1
Boron	ppm	ASTM D5185m	2.5	48	52	59
Barium	ppm	ASTM D5185m	0.0	1	0	0
Molybdenum	ppm	ASTM D5185m	0.7	42	41	90
Manganese	ppm	ASTM D5185m	0.0	1	<1	3
Magnesium	ppm	ASTM D5185m	256	478	516	40
Calcium	ppm	ASTM D5185m	2057	1641	1816	2190
Phosphorus	ppm	ASTM D5185m	935	860	943	1016
Zinc	ppm	ASTM D5185m	1223	1089	1184	1200
Sulfur	ppm	ASTM D5185m	4079	2811	3552	5035
Oxidation	Abs/.1mm	*ASTM D7414	>25	20.4	19.9	14.0
Base Number (BN)	mg KOH/g	ASTM D2896	10	9.7	9.6	5.9
Visc @ 100°C	cSt	ASTM D445	15.0	12.8	12.9	10.8



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ASC0003172
Lab Number : 06219515
Unique Number : 11097712
Test Package : CONST (Additional Tests: TBN)

Received : 25 Jun 2024
Tested : 26 Jun 2024
Diagnosed : 26 Jun 2024 - Wes Davis

160 - ASCENDUM MACHINERY INC - MILLS RIVER
 215 FANNING FIELDS RD
 MILLS RIVER, NC
 US 28759

Contact: MARK CLAUSS
 MARK.CAUSS@ASCENDUMMACHINERY.COM

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (828)687-0620
 F: (828)214-1786