

WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL




[G35729]

JOHN DEERE 210G 1FF210GXJGE520844

Diesel Engine

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (--- GAL)

			-				
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		WE0007662		
Resample at the next service interval to monitor.	Sample Date		Client Info		24 Jun 2024		
	Machine Age	hrs	Client Info		5935		
	Oil Age	hrs	Client Info		127		
	Filter Age	hrs	Client Info		127		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAD			AOTM DEGOE		_		
WEAR	Iron	ppm	ASTM D5185m		4		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>5	<1		
	Titanium	ppm	ASTM D5185m	0	<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m	>26	<1 3		
	Copper	ppm	ASTM D5185m				
	Tin Vanadium	ppm	ASTM D5185m ASTM D5185m	>4	<1 <1		
	White Metal	ppm scalar	*Visual	NONE	NONE		
	Yellow Metal		*Visual	NONE	NONE		
<u></u>	Tellow Metal	scalar	Visuai	INOINL	INONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>22	8		
	Potassium	ppm	ASTM D5185m	>20	3		
There is no indication of any contamination in the oil.	Fuel		WC Method	>2.1	<1.0		
	Water		WC Method	>0.21	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.1		
	Nitration	Abs/cm	*ASTM D7624	>20	5.7		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	19.1		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.21	NEG		
ELUID CONDITION	Co ali		ACTM DE10E	04			
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>31	1		
The BN result indicates that there is suitable alkalinity remaining in the	Boron	ppm	ASTM D5185m		287		
oil. The condition of the oil is suitable for further service.	Barium Molybdenum	ppm	ASTM D5185m		2 224		
	Manganese	ppm	ASTM D5185m ASTM D5185m		<1 <1		
	Magnesium	ppm	ASTM D5185m		714		
	Calcium	ppm ppm	ASTM D5185m		1305		
	Phosphorus	ppm	ASTM D5185m		779		
	Zinc	ppm	ASTM D5185m		998		
	Sulfur	ppm	ASTM D5185m		2822		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	14.0		
	Base Number (BN)		ASTM D2896		10.5		
	Visc @ 100°C	cSt	ASTM D445		14.0		
	1.00 @ 100 0	001	. 10 1141 0 440	10.7	17.0		







Certificate L2367

Laboratory Sample No. Unique Number : 11097714

Lab Number : 06219517

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WE0007662

Received **Tested** Diagnosed

: 25 Jun 2024 : 26 Jun 2024 : 26 Jun 2024 - Wes Davis

WARRIOR TRACTOR AND EQUIPMENT - HUNTSVILLE 25135 ONE AVIATION WAY SW MADISON, AL

US 35756 Contact: HERBERT STONE WTE013@WARRIORTRACTOR.COM

Test Package : CONST (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

T: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: