



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 350P 1FF350PAHNF000054
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (28 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0218645	JR0183812	JR0160316
Sample Date		Client Info		21 Jun 2024	28 Aug 2023	03 Feb 2023
Machine Age	hrs	Client Info		1486	938	439
Oil Age	hrs	Client Info		987	499	0
Filter Age	hrs	Client Info		987	0	0
Oil Changed		Client Info		Changed	N/A	Changed
Filter Changed		Client Info		Changed	N/A	Changed
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	37	28	37
Chromium	ppm	ASTM D5185m	>11	1	<1	<1
Nickel	ppm	ASTM D5185m	>5	10	8	6
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	<1	<1	2
Aluminum	ppm	ASTM D5185m	>31	6	4	5
Lead	ppm	ASTM D5185m	>26	2	<1	3
Copper	ppm	ASTM D5185m	>26	20	29	27
Tin	ppm	ASTM D5185m	>4	2	1	3
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION









There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>22	9	7	11
Potassium	ppm	ASTM D5185m	>20	4	3	8
Fuel	%	ASTM D3524	>2.1	<1.0	<1.0	0.4
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.4	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	9.1	8.8	8.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.0	22.8	23.6
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	<1	2	7
Boron	ppm	ASTM D5185m		145	206	245
Barium	ppm	ASTM D5185m		2	0	<1
Molybdenum	ppm	ASTM D5185m		210	241	221
Manganese	ppm	ASTM D5185m		2	1	1
Magnesium	ppm	ASTM D5185m		666	867	786
Calcium	ppm	ASTM D5185m		1796	1454	1418
Phosphorus	ppm	ASTM D5185m		820	864	782
Zinc	ppm	ASTM D5185m		1087	1106	974
Sulfur	ppm	ASTM D5185m		3016	3595	3221
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.0	18.3	19.6
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	8.1	7.8	7.9
Visc @ 100°C	cSt	ASTM D445	15.4	12.6	12.9	10.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0218645 **Received** : 25 Jun 2024
Lab Number : 06219542 **Tested** : 26 Jun 2024
Unique Number : 11097739 **Diagnosed** : 26 Jun 2024 - Don Baldrige
Test Package : CONST (Additional Tests: FuelDilution, TBN)

JRE - MANASSAS PARK
 9107 OWENS DRIVE
 MANASSAS PARK, VA
 US 20111
 Contact: DON VEST
 dvest@jamesriverequipment.com
 T: (703)631-8500
 F: (703)631-4715

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)