WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Machine Id

NOT GIVEN JR0220014 (S/N NO INFO ON SIF/BOTTLE)

Hydraulic System

{not provided} (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0220014		
	Sample Date		Client Info		24 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		17		
	Iron	ppm	ASTM D5185m	>20	0		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>10	0		
	Lead	ppm	ASTM D5185m	>10	0		
	Copper	ppm	ASTM D5185m	>75	0		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>20	0		
CONTAININATION	Potassium	ppm	ASTM D5185m		0		
The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.	Water	ррпп	WC Method		NEG		
	Particles >4µm		ASTM D7647		1647		
	Particles >6µm		ASTM D7647		305		
	Particles >14µm		ASTM D7647		31		
	Particles >21µm		ASTM D7647		8		
	Particles >38µm		ASTM D7647		0		
	Particles >71µm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		18/15/12		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	nnm	ASTM D5185m				
	Boron	ppm	ASTM D5185m		2		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm ppm	ASTM D5185m		0		
	Manganese		ASTM D5185m		0		
	Magnesium	ppm ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		108		
	Phosphorus	ppm	ASTM D5185m		682		
	Zinc	ppm	ASTM D5185m		861		
	Sulfur	ppm	ASTM D5185m		1951		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.82		
	Visc @ 40°C	cSt	ASTM D445		61.0		





Certificate L2367

Laboratory Sample No. Lab Number Unique Number : 11097781

: JR0220014 : 06219584

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received

Tested Diagnosed Test Package : CONST (Additional Tests: PQ)

: 25 Jun 2024 : 26 Jun 2024 : 26 Jun 2024 - Don Baldridge

JRE - CHARLOTTE 9550 STATESVILLE ROAD CHARLOTTE, NC US 28269

Contact: KEVIN PEARCE KPEARCE@JAMESRIVEREQUIPMENT.COM

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (704)596-6198

T: