

[00100103]

NOT GIVEN JR0216871 (S/N NO INFO ON SIF/BOTTLE)

Transmission (Manual)

TDH FLUID SAE 75W80 (--- GAL)

IDH FLUID SAE / SWOU (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0216871		
	Sample Date		Client Info		25 Jun 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		19		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		32		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>5	<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	>7	0		
	Aluminum	ppm	ASTM D5185m	>25	2		
	Lead	ppm	ASTM D5185m	>45	1		
	Copper	ppm	ASTM D5185m	>225	7		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	0:1:			105	47		
There is no indication of any contamination in the fluid.	Silicon	ppm	ASTM D5185m		17		
	Potassium	ppm	ASTM D5185m		4		
	Water	lev	WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		8		
The condition of the fluid is acceptable for the time in service.	Boron	ppm	ASTM D5185m	10	13		
	Barium	ppm	ASTM D5185m	10	0		
	Molybdenum	ppm	ASTM D5185m	10	0		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m	100	101		
	Calcium	ppm	ASTM D5185m	3500	3587		
	Phosphorus	ppm	ASTM D5185m	1150	1083		
	Zinc	ppm	ASTM D5185m	1150	1282		
	Sulfur	ppm	ASTM D5185m		4530		


Visc @ 40°C


cSt


ASTM D445 48

Contact/Location: BILL ACKER - JAMWAK

52.0







Contact/Location: BILL ACKER - JAMWAK Page 2 of 2

un25/24