
WEAR CONTAMINATION FLUID CONDITION **NORMAL NORMAL NORMAL**

[W52619 JR CASKEY]

HAMM GRW180I H2280193

Right Final Drive

GEAR OIL ISO 220 (QTS)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. NOTE: one of two samples received with same ID and sampling date.	Sample Number		Client Info		JR0224937		
	Sample Date		Client Info		21 Jun 2024		
	Machine Age	hrs	Client Info		1215		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		40		
	Iron	ppm	ASTM D5185m	>500	147		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		2		
	Nickel	ppm	ASTM D5185m		- <1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>25	3		
	Lead	ppm	ASTM D5185m	>25	1		
	Copper	ppm	ASTM D5185m	>50	2		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	\ 75	2		
	Potassium	ppm	ASTM D5185m		3		
	Water	ρρ	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	50	<1		
	Barium	ppm	ASTM D5185m		3		
	Molybdenum	ppm	ASTM D5185m		1		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m	50	6		
	Calcium	ppm	ASTM D5185m		105		
	Phosphorus	ppm	ASTM D5185m	350	255		
	Zinc	ppm	ASTM D5185m	100	34		
	Sulfur	ppm	ASTM D5185m	12500	21511		
	Visc @ 40°C	cSt	ASTM D445	220	141		





Certificate L2367

Laboratory Sample No.

Lab Number : 06219969 Unique Number : 11098166 Test Package : CONST (Additional Tests: PQ)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : JR0224937

Received **Tested**

: 25 Jun 2024 : 26 Jun 2024 Diagnosed

: 27 Jun 2024 - Jonathan Hester

JRE - ASHLAND 11047 LEADBETTER RD ASHLAND, VA US 23005

Contact: DAVID ZIEG dzieg@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (804)798-6001 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (804)798-0292