

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL

Machine Id

1BZ644GAHPLR00173 Component Front Differential

{not provided} (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

WEAR

All component wear rates are normal.

CONTAMINATION

There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0214031		
Sample Date		Client Info		24 Jun 2024		
Machine Age	hrs	Client Info		795		
Oil Age	hrs	Client Info		795		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		N/A		
Sample Status				NORMAL		
PQ		ASTM D8184		29		
Iron	nnm	ASTM D0104 ASTM D5185m	>500	29 75		
Chromium	ppm	ASTM D5185m	>10	~1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m	210	<1 <1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	2		
Copper	ppm	ASTM D5185m	>100	2 16		
Tin	ppm	ASTM D5185m	>100	<1		
Vanadium	ppm ppm	ASTM D5185m	>10	<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>75	5		
Potassium	ppm	ASTM D5185m	>20	4		
Water		WC Method	>.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Sodium	ppm	ASTM D5185m		6		
Boron	ppm	ASTM D5185m		2		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		3		
Magnesium	ppm	ASTM D5185m		97		
Calcium	ppm	ASTM D5185m		3415		
Phosphorus	ppm	ASTM D5185m		1107		
Zinc	ppm	ASTM D5185m		1292		
Sulfur	ppm	ASTM D5185m		3782		
Visc @ 40°C	cSt	ASTM D445		58.6		





