



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**JOHN DEERE 260P 1DW260PALRFB08197**  
 Component  
**Center Differential**  
 Fluid  
**JOHN DEERE HY-GARD HYD/TRANS (39 QTS)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>JR0218373</b>	---	---
Sample Date		Client Info		<b>21 Jun 2024</b>	---	---
Machine Age	hrs	Client Info		<b>515</b>	---	---
Oil Age	hrs	Client Info		<b>515</b>	---	---
Filter Age	hrs	Client Info		<b>0</b>	---	---
Oil Changed		Client Info		<b>Changed</b>	---	---
Filter Changed		Client Info		<b>None</b>	---	---
Sample Status				<b>NORMAL</b>	---	---

### WEAR

All component wear rates are normal.

PQ		ASTM D8184		<b>189</b>	---	---
Iron	ppm	ASTM D5185m	>500	<b>274</b>	---	---
Chromium	ppm	ASTM D5185m	>10	<b>3</b>	---	---
Nickel	ppm	ASTM D5185m	>10	<b>6</b>	---	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	---	---
Silver	ppm	ASTM D5185m		<b>&lt;1</b>	---	---
Aluminum	ppm	ASTM D5185m	>25	<b>3</b>	---	---
Lead	ppm	ASTM D5185m	>25	<b>&lt;1</b>	---	---
Copper	ppm	ASTM D5185m	>100	<b>83</b>	---	---
Tin	ppm	ASTM D5185m	>10	<b>4</b>	---	---
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	---	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	---	---

### CONTAMINATION






There is no indication of any contamination in the sample.

Silicon	ppm	ASTM D5185m	>75	<b>19</b>	---	---
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	---	---
Water		WC Method	>.2	<b>NEG</b>	---	---
Silt	scalar	*Visual	NONE	<b>MODER</b>	---	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	---	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	---	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	---	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	---	---
Emulsified Water	scalar	*Visual	>.2	<b>NEG</b>	---	---

### FLUID CONDITION

The condition of the sample is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<b>17</b>	---	---
Boron	ppm	ASTM D5185m	6	<b>108</b>	---	---
Barium	ppm	ASTM D5185m	0	<b>0</b>	---	---
Molybdenum	ppm	ASTM D5185m	0	<b>&lt;1</b>	---	---
Manganese	ppm	ASTM D5185m		<b>30</b>	---	---
Magnesium	ppm	ASTM D5185m	145	<b>9</b>	---	---
Calcium	ppm	ASTM D5185m	3570	<b>3282</b>	---	---
Phosphorus	ppm	ASTM D5185m	1290	<b>1257</b>	---	---
Zinc	ppm	ASTM D5185m	1640	<b>1431</b>	---	---
Sulfur	ppm	ASTM D5185m		<b>3864</b>	---	---
Visc @ 40°C	cSt	ASTM D445	57.0	<b>64.0</b>	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : JR0218373

Lab Number : 06220029

Unique Number : 11098226

Test Package : CONST ( Additional Tests: PQ )

Received : 25 Jun 2024

Tested : 26 Jun 2024

Diagnosed : 26 Jun 2024 - Sean Felton

JRE - MANASSAS PARK

9107 OWENS DRIVE

MANASSAS PARK, VA

US 20111

Contact: TECHNICIAN ACCOUNT

catherine.anastasio@wearcheck.com

T:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (703)631-4715