



WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Area

## Store 8 - Pikeville [152172] JOHN DEERE 210G 1FF210GXHKF527549

**Swing Drive** 

JOHN DEERE HY-GARD HYD/TRANS (2 GAL)

JOHN DEERE HY-GARD HYD/	TRANS (2 G	4L)					
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0046365	LEC0023635	LEC0006724
	Sample Date		Client Info		20 Jun 2024	26 Aug 2021	22 Jan 2020
	Machine Age	hrs	Client Info		2029	877	327
	Oil Age	hrs	Client Info		1152	550	327
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		Changed	Changed	Changed
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				NORMAL	NORMAL	ATTENTION
WEAR	PQ		ASTM D8184		23	29	39
	Iron	ppm	ASTM D5185m	>151	36	43	47
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1	<1	<1
	Nickel	ppm	ASTM D5185m	>10	<1	0	<1
	Titanium	ppm	ASTM D5185m		<1	0	0
	Silver	ppm	ASTM D5185m		<1	0	<1
	Aluminum	ppm	ASTM D5185m	>21	2	<1	<1
	Lead	ppm	ASTM D5185m	>51	0	0	0
	Copper	ppm	ASTM D5185m	>51	<1	0	<1
	Tin	ppm	ASTM D5185m	>10	<1	0	<1
	Vanadium	ppm	ASTM D5185m		<1	0	0
	White Metal	scalar	*Visual	NONE	NONE	VLITE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>31	12	17	18
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	2	0	1
	Water		WC Method	>0.1	NEG	NEG	NEG
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	NONE	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
	Odor	scalar	*Visual	NORML	NORML	NORML	NORML
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	2	2	0
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	33	87	94
The condition of the on is acceptable for the time in service.	Barium	ppm	ASTM D5185m	0	0	2	9
	Molybdenum	ppm	ASTM D5185m	0	1	0	<1
	Manganese	ppm	ASTM D5185m		1	1	2
	Magnesium	ppm	ASTM D5185m	145	72	<1	<1
	Calcium	ppm	ASTM D5185m	3570	2491	29	21
	Phosphorus	ppm	ASTM D5185m	1290	976	435	535
	Zinc	ppm	ASTM D5185m	1640	964	9	0
	Sulfur	ppm	ASTM D5185m		6415	11380	14355
	Visc @ 40°C	cSt	ASTM D445		77.6	186	185
Report Id: LESMAROH [WUSCAR] 06220064 (Generated: 06/30/2024 16:27:28) Rev: 1		Sı	ubmitted By:	STORE	8 - PIKEVILI	LE - MICHEL	LE LITTLE







Laboratory Sample No.

Lab Number : 06220064 Unique Number : 11098261

: LEC0046365

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 25 Jun 2024 **Tested** : 26 Jun 2024 : 27 Jun 2024 - Sean Felton

Diagnosed Test Package : CONST ( Additional Tests: PQ )

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL KendalLeanne@lec1.com

T: F: (740)373-5570

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)