

[42438]

WEAR NORMAL CONTAMINATION ABNORMAL FLUID CONDITION NORMAL



VOLVO A30G 752368

Hydraulic System

VOLVO SUPER HYDRAULIC OIL 46 (--- GAL)

RECOMMENDATION

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

W	R

All component wear rates are normal.

CONTAMINATION


Moderate concentration of visible dirt/debris present in the oil.

					_
		\mathbf{cor}			
FLUI	U.	COI	VU.	ITION	

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VCP439858		
Sample Date		Client Info		21 Jun 2024		
Machine Age	hrs	Client Info		2288		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Changed		
Sample Status				ABNORMAL		
Iron		ASTM D5185m	. 50			
Iron	ppm		>50	7		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m		2		
Lead	ppm	ASTM D5185m	>20	2		
Copper	ppm	ASTM D5185m	>150	4		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>20	6		
Potassium	ppm	ASTM D5185m	>20	2		
Water	lele	WC Method	>0.1	– NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Sodium	ppm	ASTM D5185m		2		
Boron	ppm	ASTM D5185m	14	15		
Barium	ppm	ASTM D5185m	0.0	0		
Molybdenum	ppm	ASTM D5185m	0.0	5		
Manganese	ppm	ASTM D5185m	0.0	<1		
Magnesium	ppm	ASTM D5185m	2.6	38		
Calcium	ppm	ASTM D5185m	49	317		
Phosphorus	ppm	ASTM D5185m	354	352		
Zinc	ppm	ASTM D5185m	419	406		
Sulfur	ppm	ASTM D5185m	3719	2464		
Acid Number (AN)	mg KOH/g	ASTM D8045		0.40		
Visc @ 40°C	cSt	ASTM D445	46	43.3		
		<u> </u>				

Contact/Location: TAMI BROWDER - VOLVO0013



215 - ASCENDUM MACHINERY INC - CAYCE Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : VCP439858 Received : 25 Jun 2024 2303 AIRPORT BLVD Lab Number : 06220355 Tested CAYCE, SC : 27 Jun 2024 Unique Number : 11098552 Diagnosed : 27 Jun 2024 - Doug Bogart US 29033 Test Package : MOB 2 Contact: TAMI BROWDER Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. tami.browder@ascendummachinery.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (803)923-2138 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (803)791-9920

Contact/Location: TAMI BROWDER - VOLVO0013 Page 2 of 2