



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Area

**[W68113]**

Machine Id

**VOLVO EC350E C350E310336**

Component

**Diesel Engine**

Fluid

**JOHN DEERE ENGINE OIL PLUS 50 II 0W40 (13 GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor. ( Customer Sample Comment: W68113 )

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>JR0219740</b>	JR0206728	---
Sample Date		Client Info		<b>25 Jun 2024</b>	11 Apr 2024	---
Machine Age	hrs	Client Info		<b>8800</b>	8473	---
Oil Age	hrs	Client Info		<b>327</b>	8473	---
Filter Age	hrs	Client Info		<b>0</b>	0	---
Oil Changed		Client Info		<b>Changed</b>	Changed	---
Filter Changed		Client Info		<b>Changed</b>	Changed	---
Sample Status				<b>NORMAL</b>	ABNORMAL	---

### WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	<b>4</b>	14	---
Chromium	ppm	ASTM D5185m	>20	<b>0</b>	<1	---
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	<1	---
Titanium	ppm	ASTM D5185m		<b>0</b>	0	---
Silver	ppm	ASTM D5185m	>3	<b>0</b>	0	---
Aluminum	ppm	ASTM D5185m	>20	<b>4</b>	2	---
Lead	ppm	ASTM D5185m	>40	<b>&lt;1</b>	6	---
Copper	ppm	ASTM D5185m	>330	<b>3</b>	10	---
Tin	ppm	ASTM D5185m	>15	<b>0</b>	1	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---

### CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	<b>7</b>	9	---
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	1	---
Fuel		WC Method	>5	<b>&lt;1.0</b>	<1.0	---
Water		WC Method	>0.2	<b>NEG</b>	NEG	---
Glycol		WC Method		<b>NEG</b>	NEG	---
Soot %	%	*ASTM D7844	>3	<b>0.1</b>	0.1	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>8.8</b>	13.6	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>22.2</b>	28.5	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	---

### FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<b>9</b>	2	---
Boron	ppm	ASTM D5185m		<b>209</b>	70	---
Barium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	---
Molybdenum	ppm	ASTM D5185m		<b>221</b>	61	---
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	<1	---
Magnesium	ppm	ASTM D5185m		<b>792</b>	572	---
Calcium	ppm	ASTM D5185m		<b>1464</b>	1707	---
Phosphorus	ppm	ASTM D5185m		<b>970</b>	1135	---
Zinc	ppm	ASTM D5185m		<b>1126</b>	1256	---
Sulfur	ppm	ASTM D5185m		<b>3515</b>	3166	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>17.4</b>	31.2	---
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	<b>7.8</b>	▲ 3.1	---
Visc @ 100°C	cSt	ASTM D445	14	<b>12.8</b>	13.5	---



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0219740 **Received** : 26 Jun 2024  
**Lab Number** : 06220827 **Tested** : 27 Jun 2024  
**Unique Number** : 11099024 **Diagnosed** : 27 Jun 2024 - Sean Felton  
**Test Package** : CONST ( Additional Tests: TBN )

**JRE - CHARLOTTE**  
 9550 STATESVILLE ROAD  
 CHARLOTTE, NC  
 US 28269  
 Contact: CHARLOTTE SHOP  
 myoung@jamesriverequipment.com  
 T: (704)597-0211  
 F: (704)596-6198

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)