



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
BRIAN A NAPACK
Machine Id
[BRIAN A NAPACK] 007 640349-7
Component
Port Genset
Fluid
CHEVRON DELO 400 LE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0068271	MW0068344	MW0061489
Sample Date		Client Info		24 May 2024	30 Mar 2024	21 Jan 2024
Machine Age	hrs	Client Info		9527	8693	7960
Oil Age	hrs	Client Info		433	330	408
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	11	17	11
Chromium	ppm	ASTM D5185m	>4	<1	<1	0
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>12	3	4	4
Lead	ppm	ASTM D5185m	>17	<1	5	5
Copper	ppm	ASTM D5185m	>70	2	5	4
Tin	ppm	ASTM D5185m	>15	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	5	7
Potassium	ppm	ASTM D5185m	>20	2	<1	<1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.4	0.4	0.3
Nitration	Abs/cm	*ASTM D7624	>20	8.0	8.0	8.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.8	24.1	24.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	<1	<1
Boron	ppm	ASTM D5185m		303	331	330
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		131	138	131
Manganese	ppm	ASTM D5185m		3	3	3
Magnesium	ppm	ASTM D5185m		608	701	665
Calcium	ppm	ASTM D5185m		1564	1770	1544
Phosphorus	ppm	ASTM D5185m	1200	692	787	741
Zinc	ppm	ASTM D5185m	1300	952	961	847
Sulfur	ppm	ASTM D5185m	3200	2568	3225	2909
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.9	18.7	19.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	9.0	8.7	9.0
Visc @ 100°C	cSt	ASTM D445	15.7	13.2	13.5	13.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0068271
Lab Number : 06220999
Unique Number : 11099196
Test Package : MAR 2
Received : 26 Jun 2024
Tested : 27 Jun 2024
Diagnosed : 27 Jun 2024 - Wes Davis

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003

Contact: JUSTIN WHEELER
 justin.wheeler@ingrambarga.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (615)695-3697