

Machine Id **1688-8123063** Component **Compressor** Fluid **KAESER SIGMA (OEM) M-460 (--- GAL)**

RECOMMENDATION

We recommend you service the filters on this component. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

WEAR

All component wear rates are normal.

CONTAMINATION

Moderate concentration of visible dirt/debris present in the oil.

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		Y2K0001563		
Sample Date		Client Info		20 Jun 2024		
Machine Age	hrs	Client Info		8280		
Oil Age	hrs	Client Info		800		
Filter Age	hrs	Client Info		800		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Not Changd		
Sample Status				ABNORMAL		
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>3	0		
Titanium	ppm	ASTM D5185m	>3	0		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>10	0		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>50	5		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>25	1		
Potassium	ppm	ASTM D5185m	>20	2		
Water	%	ASTM D5185III	>2.05	2 0.348		
ppm Water	ppm	ASTM D6304	>500	3480		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.05	0.2%		
	Scalal	visuai	>0.05	0.2 /0		
Sodium	ppm	ASTM D5185m		9		
Boron	ppm	ASTM D5185m	0	<1		
Barium	ppm	ASTM D5185m	90	25		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	100	46		
Calcium	ppm	ASTM D5185m	0	0		
Phosphorus	ppm	ASTM D5185m	0	10		
Zinc	ppm	ASTM D5185m	0	4		
Sulfur	ppm	ASTM D5185m	23500	22096		
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.40		
Vier @ 4000	- C+		45	47.0		

WEAR NORMAL CONTAMINATION ABNORMAL FLUID CONDITION NORMAL


Visc @ 40°C


cSt

ASTM D445 45

Contact/Location: Service Manager - NEWABE

47.6





Contact/Location: Service Manager - NEWABE Page 2 of 2