



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**JOHN DEERE 948L 1DW948LXJGF674846**

Component  
**Transmission (Manual)**

Fluid  
**JOHN DEERE HY-GARD HYD/TRANS (--- GAL)**

### RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>JR0212106</b>	JR0124145	JR0067669
Sample Date		Client Info		<b>25 Jun 2024</b>	13 Apr 2022	04 Dec 2020
Machine Age	hrs	Client Info		<b>9500</b>	6031	1496
Oil Age	hrs	Client Info		<b>0</b>	1	1496
Filter Age	hrs	Client Info		<b>0</b>	1	1496
Oil Changed		Client Info		<b>Not Changed</b>	Not Changed	Not Changed
Filter Changed		Client Info		<b>Not Changed</b>	Not Changed	Not Changed
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

### WEAR

All component wear rates are normal.

PQ		ASTM D8184	>95	<b>19</b>	12	20
Iron	ppm	ASTM D5185m	>200	<b>34</b>	3	21
Chromium	ppm	ASTM D5185m	>5	<b>&lt;1</b>	<1	0
Nickel	ppm	ASTM D5185m	>5	<b>0</b>	0	<1
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m	>7	<b>&lt;1</b>	0	<1
Aluminum	ppm	ASTM D5185m	>25	<b>3</b>	2	<1
Lead	ppm	ASTM D5185m	>45	<b>&lt;1</b>	<1	0
Copper	ppm	ASTM D5185m	>225	<b>11</b>	<1	7
Tin	ppm	ASTM D5185m	>10	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

### CONTAMINATION







There is no indication of any contamination in the fluid.

Silicon	ppm	ASTM D5185m	>125	<b>5</b>	6	5
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	2	6
Water		WC Method	>0.1	<b>NEG</b>	NEG	NEG
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	<b>NEG</b>	NEG	NEG

### FLUID CONDITION

The condition of the fluid is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<b>3</b>	3	3
Boron	ppm	ASTM D5185m	6	<b>1</b>	<1	2
Barium	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	<1
Molybdenum	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	0
Manganese	ppm	ASTM D5185m		<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	145	<b>87</b>	100	92
Calcium	ppm	ASTM D5185m	3570	<b>3263</b>	3409	3413
Phosphorus	ppm	ASTM D5185m	1290	<b>1092</b>	1066	946
Zinc	ppm	ASTM D5185m	1640	<b>1243</b>	1313	1167
Sulfur	ppm	ASTM D5185m		<b>3859</b>	2828	2717
Visc @ 40°C	cSt	ASTM D445	57.0	<b>49.0</b>	56.6	48.3



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0212106 **Received** : 26 Jun 2024  
**Lab Number** : 06221461 **Tested** : 27 Jun 2024  
**Unique Number** : 11099658 **Diagnosed** : 27 Jun 2024 - Wes Davis  
**Test Package** : CONST ( Additional Tests: PQ )

**JRE - ASHLAND**  
 11047 LEADBETTER RD  
 ASHLAND, VA  
 US 23005  
 Contact: DAVID ZIEG  
 dzieg@jamesriverequipment.com  
 T: (804)798-6001  
 F: (804)798-0292

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)