



# OIL ANALYSIS REPORT

WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**VOLVO A30G#301 (S/N 740069)**  
 Component  
**Center Axle**  
 Fluid  
**MOBIL 75W90 (--- GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>TLY0002474</b>	TLY0001639	---
Sample Date		Client Info		<b>21 Jun 2024</b>	30 Oct 2023	---
Machine Age	hrs	Client Info		<b>7874</b>	7291	---
Oil Age	hrs	Client Info		<b>7291</b>	1291	---
Filter Age	hrs	Client Info		<b>7291</b>	1291	---
Oil Changed		Client Info		<b>Not Changd</b>	Not Changd	---
Filter Changed		Client Info		<b>Not Changd</b>	Not Changd	---
Sample Status				<b>NORMAL</b>	ATTENTION	---

## WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	<b>205</b>	179	---
Chromium	ppm	ASTM D5185m	>10	<b>3</b>	2	---
Nickel	ppm	ASTM D5185m	>10	<b>2</b>	1	---
Titanium	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
Silver	ppm	ASTM D5185m		<b>&lt;1</b>	0	---
Aluminum	ppm	ASTM D5185m	>25	<b>2</b>	0	---
Lead	ppm	ASTM D5185m	>25	<b>&lt;1</b>	0	---
Copper	ppm	ASTM D5185m	>50	<b>18</b>	13	---
Tin	ppm	ASTM D5185m	>10	<b>1</b>	<1	---
Vanadium	ppm	ASTM D5185m		<b>&lt;1</b>	<1	---
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	---

## CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>75	<b>5</b>	4	---
Potassium	ppm	ASTM D5185m	>20	<b>1</b>	0	---
Water		WC Method	>0.2	<b>NEG</b>	NEG	---
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	---
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	---
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	---

## FLUID CONDITION


Confirm oil type. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		<b>0</b>	3	---
Boron	ppm	ASTM D5185m		<b>197</b>	193	---
Barium	ppm	ASTM D5185m		<b>1</b>	0	---
Molybdenum	ppm	ASTM D5185m		<b>1</b>	0	---
Manganese	ppm	ASTM D5185m		<b>5</b>	4	---
Magnesium	ppm	ASTM D5185m		<b>3</b>	0	---
Calcium	ppm	ASTM D5185m		<b>104</b>	96	---
Phosphorus	ppm	ASTM D5185m		<b>2065</b>	2250	---
Zinc	ppm	ASTM D5185m		<b>50</b>	44	---
Sulfur	ppm	ASTM D5185m		<b>27328</b>	26670	---


### Ferrous Alloys



### Non-ferrous Metals



### Viscosity @ 40°C



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : TLY0002474  
**Lab Number** : 06221886  
**Unique Number** : 11100083  
**Test Package** : CONST

**Received** : 26 Jun 2024  
**Tested** : 29 Jun 2024  
**Diagnosed** : 29 Jun 2024 - Don Baldrige

**GAINES & COMPANY**  
 112 WESTMINISTER RD  
 REISTERSTOWN, MD  
 US 21136

Contact: LANCE TANCRAITOR  
 ltancraitor@gainesandco.com  
 T: (410)833-9833

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: