WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Machine Id

PETERBILT PETERBILT 567 ROLLOFF-8078022

Diesel Engine

PETRO CANADA DURON SHP 15W40 (44 QTS)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		PE0003940		
	Sample Date		Client Info		10 Jun 2024		
	Machine Age	hrs	Client Info		21522		
	Oil Age	hrs	Client Info		430		
	Filter Age	hrs	Client Info		430		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		Changed		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>100	6		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	<1		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m	>3	0		
	Aluminum	ppm	ASTM D5185m		4		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		<1		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m	710	<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
				NONL			
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	5		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	7		
	Fuel		WC Method	>5	<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol		WC Method		NEG		
	Soot %	%	*ASTM D7844	>3	0.2		
	Nitration	Abs/cm	*ASTM D7624	>20	7.7		
	Sulfation	Abs/.1mm	*ASTM D7415	>30	18.4		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		5		
LOID CONDITION	Boron	ppm	ASTM D5185m	0	17		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		41		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		913		
	Calcium	ppm	ASTM D5185m		1178		
	Phosphorus		ASTM D5185m		1007		
	Zinc	ppm	ASTM D5185m		1183		
		ppm					
	Sulfur	ppm Abo/1mm	ASTM D5185m		3542		
	Oxidation Base Number (BN)	Abs/.1mm mg KOH/g	*ASTM D7414 ASTM D2896		14.0 8.5		







Certificate L2367

Report Id: CEDSEA [WUSCAR] 06222208 (Generated: 06/28/2024 15:03:42) Rev: 1

Laboratory Sample No.

: PE0003940 Lab Number : 06222208 Unique Number : 11100405

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

: 27 Jun 2024 Diagnosed

: 28 Jun 2024

: 28 Jun 2024 - Don Baldridge Test Package: FLEET (Additional Tests: FT-IR, ICP, KV100, SCREEN, TBN)

7343 E MARINGAL WAY S SEATTLE, WA US 98108 Contact: CRAIG BOWEN craigb@cgcompost.com T: (877)764-5748

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **CEDAR GROVE**