WEAR CONTAMINATION **FLUID CONDITION** **NORMAL NORMAL NORMAL**

[X18706]

VOLVO A40G 353135



VOLVO SUPER GEAR OIL 7	3W-60-GO 102 ((G	AL)				
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VCP433025		
	Sample Date		Client Info		17 Jun 2024		
	Machine Age	hrs	Client Info		4110		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAR	Iron	ppm	ASTM D5185m	>900	134		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>20	2		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	3		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>150	1		
	Tin	ppm	ASTM D5185m	>20	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	4		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		2		
	Water	1-1-	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		252		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		2		
	Manganese	ppm	ASTM D5185m		5		
	Magnesium	ppm	ASTM D5185m		<1		
	Calcium	ppm	ASTM D5185m		2		
	Phosphorus	ppm	ASTM D5185m		2613		
	Zinc	ppm	ASTM D5185m		6		
	Sulfur	ppm	ASTM D5185m		31957		
	Visc @ 40°C	cSt	ASTM D445		50.5		





Certificate L2367

Laboratory Sample No.

: VCP433025 Lab Number : 06222603 Unique Number : 11100800 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 27 Jun 2024 **Tested** : 28 Jun 2024

Diagnosed : 29 Jun 2024 - Don Baldridge

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

APAC BENTON

393 OREILLY RD BENTON, MS US 39039

Contact: WILL RATLIFF will.ratliffjr@apac.com

T: (601)397-3696