
WEAR CONTAMINATION **FLUID CONDITION** **NORMAL NORMAL NORMAL**





Machine Id **VOLVO EC350 314743**


Right Final Drive

GEAR OIL SAE 80W90 (GAL)						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.	Sample Number		Client Info		ASC0011050		
	Sample Date		Client Info		25 Jun 2024		
	Machine Age	hrs	Client Info		572		
	Oil Age	hrs	Client Info		572		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>500	241		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	3		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	3		
	Lead	ppm	ASTM D5185m	>25	<1		
	Copper	ppm	ASTM D5185m	>50	<1		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	\75	8		
	Potassium	ppm	ASTM D5185m		2		
There is no indication of any contamination in the oil.	Water	le le	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	8		
	Barium	ppm	ASTM D5185m	200	1		
	Molybdenum	ppm	ASTM D5185m	12	<1		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m	12	2		
	Calcium	ppm	ASTM D5185m	150	8		
	Phosphorus	ppm	ASTM D5185m	1650	401		
	Zinc	ppm	ASTM D5185m	125	14		
	Sulfur	ppm	ASTM D5185m	22500	17929		
	Visc @ 40°C	cSt	ASTM D445	143	172		











Laboratory Sample No.

: ASC0011050 Lab Number : 06222632

Unique Number : 11100829

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 27 Jun 2024 **Tested** : 28 Jun 2024 Diagnosed

: 28 Jun 2024 - Wes Davis

113 - ASCENDUM MACHINERY INC - GARNER 3561 JONES SAUSAGE ROAD

GARNER, NC US 27529

F: (919)661-9038

Test Package : CONST Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

trent.broadwell@ascendummachinery.com T: (919)661-8817

Contact: TRENT BROADWELL

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)