



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
BOWERMAN - ORANGE COUNTY CA
Machine Id
CATERPILLAR BOW 7
Component
Biogas Engine
Fluid
MOBIL PEGASUS 605 (480 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0848337	WC0848233	WC0848219
Sample Date		Client Info		25 Jun 2024	12 Jun 2024	06 May 2024
Machine Age	hrs	Client Info		66129	65830	65026
Oil Age	hrs	Client Info		1628	1329	524
Filter Age	hrs	Client Info		1628	1329	524
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Filter Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>20	2	<1	0
Chromium	ppm	ASTM D5185m	>5	<1	0	<1
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>5	<1	0	0
Aluminum	ppm	ASTM D5185m	>15	2	2	2
Lead	ppm	ASTM D5185m	>20	<1	0	0
Copper	ppm	ASTM D5185m	>15	0	0	0
Tin	ppm	ASTM D5185m	>5	2	2	3
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION













There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>150	22	18	13
Potassium	ppm	ASTM D5185m	>20	0	0	1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0	0	0
Nitration	Abs/cm	*ASTM D7624	>20	4.1	4.0	3.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.3	16.6	16.7
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	1	<1
Boron	ppm	ASTM D5185m		69	69	125
Barium	ppm	ASTM D5185m		0	0	1
Molybdenum	ppm	ASTM D5185m		2	0	0
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		14	2	8
Calcium	ppm	ASTM D5185m		1759	1783	1626
Phosphorus	ppm	ASTM D5185m		427	419	448
Zinc	ppm	ASTM D5185m		527	549	544
Sulfur	ppm	ASTM D5185m		3962	4165	4448
Oxidation	Abs/.1mm	*ASTM D7414	>25	11.1	10.7	9.9
Acid Number (AN)	mg KOH/g	ASTM D8045		1.38	0.75	0.61
Base Number (BN)	mg KOH/g	ASTM D2896	7.1	4.43	4.47	5.13
Visc @ 100°C	cSt	ASTM D445	13.3	14.7	14.6	14.5



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0848337
Lab Number : 06222879
Unique Number : 11101076
Test Package : MOB 2

Received : 27 Jun 2024
Tested : 28 Jun 2024
Diagnosed : 29 Jun 2024 - Don Baldrige

MONTAUK ENERGY CAPITAL LLC (TEXAS) LP
 1412 N SAM HOUSTON PKWY E, SUITE 100
 HOUSTON, TX
 US 77032

Contact: DAMON MCCLENAN
 dmcclenan@montaukenergy.com

T: (713)781-1126
 F: (713)781-1127

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)