



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
WESTERN STAR T27
Component
Diesel Engine
Fluid
SHELL 15W40 (36 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		RW0004649	RW0004647	RW0004654
Sample Date		Client Info		19 Jun 2024	08 Mar 2024	08 Dec 2023
Machine Age	mls	Client Info		781919	772184	763476
Oil Age	mls	Client Info		10000	8708	12719
Filter Age	mls	Client Info		10000	8708	12719
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	54	35	71
Chromium	ppm	ASTM D5185m	>20	1	0	2
Nickel	ppm	ASTM D5185m	>2	<1	0	<1
Titanium	ppm	ASTM D5185m	>2	5	15	27
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>25	3	2	3
Lead	ppm	ASTM D5185m	>40	5	1	8
Copper	ppm	ASTM D5185m	>330	6	4	8
Tin	ppm	ASTM D5185m	>15	<1	0	2
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION














There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	4	6
Potassium	ppm	ASTM D5185m	>20	2	0	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.9	0.5	0.9
Nitration	Abs/cm	*ASTM D7624	>20	11.8	11.0	12.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	25.7	23.8	28.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>150	3	0	3
Boron	ppm	ASTM D5185m		51	57	56
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		75	54	52
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m		281	344	396
Calcium	ppm	ASTM D5185m		2563	2099	1887
Phosphorus	ppm	ASTM D5185m		1275	1120	1171
Zinc	ppm	ASTM D5185m		1514	1316	1373
Sulfur	ppm	ASTM D5185m		4931	4491	3787
Oxidation	Abs/.1mm	*ASTM D7414	>25	21.5	20.4	25.4
Base Number (BN)	mg KOH/g	ASTM D2896		8.46	7.77	7.90
Visc @ 100°C	cSt	ASTM D445		14.1	13.7	14.5



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RW0004649 **Received** : 27 Jun 2024
Lab Number : 06222892 **Tested** : 30 Jun 2024
Unique Number : 11101089 **Diagnosed** : 30 Jun 2024 - Don Baldrige
Test Package : MOB 2 (Additional Tests: TAN Man)

ROTHIG FOREST PRODUCTS, INC.
 PO BOX 340
 LUTHER, MI
 US 49656
 Contact: DOUG NELSON
 ROTHIGFORESTPRODUCTS@GMAIL.COM
 T: (231)266-8292
 F: (231)266-8578

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)