



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
824023
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0119875	GFL0097828	GFL0097850
Sample Date		Client Info		24 Jun 2024	17 Apr 2024	21 Mar 2024
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		600	600	515
Filter Age	hrs	Client Info		600	600	515
Oil Changed		Client Info		N/A	N/A	N/A
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	29	12	18
Chromium	ppm	ASTM D5185m	>5	2	1	1
Nickel	ppm	ASTM D5185m	>2	2	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	<1	<1	0
Aluminum	ppm	ASTM D5185m	>30	5	3	3
Lead	ppm	ASTM D5185m	>30	0	1	0
Copper	ppm	ASTM D5185m	>150	2	1	<1
Tin	ppm	ASTM D5185m	>5	0	1	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	9	10	5
Potassium	ppm	ASTM D5185m	>20	4	2	0
Fuel		WC Method	>5	<1.0	▲ 3.5	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.8	0.5
Nitration	Abs/cm	*ASTM D7624	>20	8.3	6.9	7.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.3	22.3	19.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		5	1	4
Boron	ppm	ASTM D5185m	0	4	● 327	<1
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	60	59	75	53
Manganese	ppm	ASTM D5185m	0	1	<1	0
Magnesium	ppm	ASTM D5185m	1010	998	● 407	931
Calcium	ppm	ASTM D5185m	1070	1087	1265	1003
Phosphorus	ppm	ASTM D5185m	1150	1066	1005	875
Zinc	ppm	ASTM D5185m	1270	1342	1095	1169
Sulfur	ppm	ASTM D5185m	2060	3758	3281	3323
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.6	17.1	17.3
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	8.3	6.6	8.2
Visc @ 100°C	cSt	ASTM D445	15.4	13.9	▲ 11.7	13.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0119875
Lab Number : 06223046
Unique Number : 11101243
Test Package : FLEET
Received : 27 Jun 2024
Tested : 28 Jun 2024
Diagnosed : 30 Jun 2024 - Don Baldrige

GFL Environmental - 958 - Tri County HC Morton
 1090 W. Jefferson St.
 Morton, IL
 US 61550
 Contact: Bryan Link
 blink@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)