



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 350P 1FF350PAHPF000543
 Component
Diesel Engine
 Fluid
JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (29 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0225740	JR0211324	JR0195738
Sample Date		Client Info		26 Jun 2024	27 Mar 2024	06 Dec 2023
Machine Age	hrs	Client Info		1992	1467	963
Oil Age	hrs	Client Info		525	503	508
Filter Age	hrs	Client Info		525	503	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				NORMAL	NORMAL	ATTENTION

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>51	32	30	32
Chromium	ppm	ASTM D5185m	>11	<1	<1	<1
Nickel	ppm	ASTM D5185m	>5	3	4	8
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	<1	0	0
Aluminum	ppm	ASTM D5185m	>31	4	5	3
Lead	ppm	ASTM D5185m	>26	2	<1	1
Copper	ppm	ASTM D5185m	>26	6	11	40
Tin	ppm	ASTM D5185m	>4	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>22	9	7	9
Potassium	ppm	ASTM D5185m	>20	1	0	3
Fuel		WC Method	>2.1	<1.0	<1.0	<1.0
Water		WC Method	>0.21	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.5	0.4	0.4
Nitration	Abs/cm	*ASTM D7624	>20	9.0	8.9	8.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.6	23.4	24.1
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.21	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>31	2	2	0
Boron	ppm	ASTM D5185m		113	138	143
Barium	ppm	ASTM D5185m		<1	0	4
Molybdenum	ppm	ASTM D5185m		251	202	208
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		907	748	608
Calcium	ppm	ASTM D5185m		1724	1659	1724
Phosphorus	ppm	ASTM D5185m		969	767	877
Zinc	ppm	ASTM D5185m		1254	1033	1032
Sulfur	ppm	ASTM D5185m		3734	3163	2850
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.5	19.2	18.7
Base Number (BN)	mg KOH/g	ASTM D2896	13.6	7.9	8.0	8.0
Visc @ 100°C	cSt	ASTM D445	15.4	13.4	13.15	12.3


FT-IR (Direct Trend)




Ferrous Alloys




Base Number




Non-ferrous Metals




Viscosity @ 100°C



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0225740 **Received** : 28 Jun 2024
Lab Number : 06223311 **Tested** : 01 Jul 2024
Unique Number : 11101508 **Diagnosed** : 01 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

B & S SITE DEVELOPMENT
 7800 PINEY BRANCH LANE
 BRISTOW, VA
 US 20136

Contact: DANNY HUFF
 dhuff@bandssite.com
 T: (540)270-3203
 F: (703)753-0605

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)