



| | |
|-----------------|---------------|
| WEAR | NORMAL |
| CONTAMINATION | NORMAL |
| FLUID CONDITION | NORMAL |



Machine Id
720009
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

| Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
|----------------|-----|-------------|-----------|--------------------|-------------|-------------|
| Sample Number | | Client Info | | GFL0118150 | GFL0108379 | GFL0071277 |
| Sample Date | | Client Info | | 25 Jun 2024 | 20 Mar 2024 | 07 Aug 2023 |
| Machine Age | hrs | Client Info | | 31903 | 31224 | 33379 |
| Oil Age | hrs | Client Info | | 679 | 0 | 33379 |
| Filter Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | Changed | Changed | Not Changd |
| Filter Changed | | Client Info | | Changed | Changed | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |

WEAR

All component wear rates are normal.

| | | | | | | |
|--------------|--------|-------------|------|--------------|------|------|
| Iron | ppm | ASTM D5185m | >120 | 5 | 5 | 8 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | <1 | <1 |
| Nickel | ppm | ASTM D5185m | >5 | 0 | <1 | <1 |
| Titanium | ppm | ASTM D5185m | >2 | <1 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 2 | 2 | 6 |
| Lead | ppm | ASTM D5185m | >40 | <1 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >330 | 1 | 1 | 1 |
| Tin | ppm | ASTM D5185m | >15 | 0 | 0 | <1 |
| Vanadium | ppm | ASTM D5185m | | <1 | <1 | 0 |
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |

CONTAMINATION








There is no indication of any contamination in the oil.

| | | | | | | |
|------------------|----------|-------------|-------|----------------|-------|-------|
| Silicon | ppm | ASTM D5185m | >25 | 3 | 3 | 3 |
| Potassium | ppm | ASTM D5185m | >20 | 2 | 17 | <1 |
| Fuel | | WC Method | >3.0 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| Soot % | % | *ASTM D7844 | >4 | 0.3 | 0.2 | 0.3 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 9.9 | 9.4 | 9.9 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 19.3 | 18.5 | 19.6 |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| | | | | | | |
|------------------|----------|-------------|------|--------------|------|------|
| Sodium | ppm | ASTM D5185m | | 2 | 31 | 3 |
| Boron | ppm | ASTM D5185m | 0 | 1 | 2 | 0 |
| Barium | ppm | ASTM D5185m | 0 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 60 | 58 | 56 | 62 |
| Manganese | ppm | ASTM D5185m | 0 | <1 | 0 | <1 |
| Magnesium | ppm | ASTM D5185m | 1010 | 998 | 960 | 992 |
| Calcium | ppm | ASTM D5185m | 1070 | 1097 | 1088 | 1095 |
| Phosphorus | ppm | ASTM D5185m | 1150 | 1090 | 949 | 1075 |
| Zinc | ppm | ASTM D5185m | 1270 | 1343 | 1328 | 1280 |
| Sulfur | ppm | ASTM D5185m | 2060 | 3742 | 3736 | 3726 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 17.3 | 16.7 | 17.6 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 9.8 | 8.1 | 7.6 | 7.6 |
| Visc @ 100°C | cSt | ASTM D445 | 15.4 | 13.4 | 13.7 | 13.5 |



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0118150
Lab Number : 06223328
Unique Number : 11101525
Test Package : FLEET

Received : 28 Jun 2024
Tested : 01 Jul 2024
Diagnosed : 01 Jul 2024 - Wes Davis

GFL Environmental - 932 - Muskego HC
 W144 S6400 College Ct.
 Muskego, WI
 US 53150

Contact: Brian Schlomann
 brian.schlomann@gflenv.com
 T: (262)510-4586

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: