

WEAR CONTAMINATION FLUID CONDITION

ABNORMAL NORMAL NORMAL

Area

Store 4 - Fairmont


JOHN%252525252525252 1FF210GXLNF530390

Right Propel Gearbox

JOHN DEERE HY-GARD HYD/TRANS (2 GAL)

JOHN DEERE HY-GARD HYD/TRANS (2 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0050146	LEC0045279	
	Sample Date		Client Info		26 Jun 2024	04 Oct 2023	
	Machine Age	hrs	Client Info		841	527	
	Oil Age	hrs	Client Info		314	527	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	N/A	
	Sample Status				ABNORMAL	NORMAL	
WEAR	PQ		ASTM D8184		101	315	
Gear wear is indicated. All other component wear rates are normal.	Iron	ppm	ASTM D5185m	>200	^ 205	424	
	Chromium	ppm	ASTM D5185m	>10	4	8	
	Nickel	ppm	ASTM D5185m	>10	1	0	
	Titanium	ppm	ASTM D5185m		<1	<1	
	Silver	ppm	ASTM D5185m		<1	<1	
	Aluminum	ppm	ASTM D5185m		2	1	
	Lead	ppm	ASTM D5185m		0	0	
	Copper	ppm	ASTM D5185m		2	1	
	Tin	ppm	ASTM D5185m		0	<1	
	Vanadium	ppm	ASTM D5185m		<1	<1	
	White Metal	scalar	*Visual	NONE	NONE	MODER	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m		18	23	
	Potassium	ppm	ASTM D5185m	>20	5	2	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	LIGHT	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m		2	<1	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	33	67	
	Barium	ppm	ASTM D5185m	0	<1	7	
	Molybdenum	ppm	ASTM D5185m	0	5	0	
	Manganese	ppm	ASTM D5185m		4	8	
	Magnesium	ppm	ASTM D5185m	145	103	3	
	Calcium	ppm	ASTM D5185m	3570	2794	15	
	Phosphorus	ppm	ASTM D5185m	1290	975	501	
	Zinc	ppm	ASTM D5185m	1640	1035	23	
	Sulfur	ppm	ASTM D5185m		7100	14173	
	Visc @ 40°C	cSt	ASTM D445	57.0	69.0	185	

Submitted By: JOHN MARTIN





Laboratory Sample No.

Lab Number : 06223728 Unique Number : 11101925

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0050146

Received : 28 Jun 2024 **Tested** : 29 Jun 2024 Diagnosed

: 30 Jun 2024 - Don Baldridge

Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL

KendalLeanne@lec1.com T:

F: (740)373-5570

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)