



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
JOHN DEERE 350P 1FF350PAHPF000543
 Component
Left Final Drive
 Fluid
JOHN DEERE GL-5 80W90 (10 QTS)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0225741	JR0211328	JR0195740
Sample Date		Client Info		26 Jun 2024	27 Mar 2024	06 Dec 2023
Machine Age	hrs	Client Info		1992	1467	963
Oil Age	hrs	Client Info		1992	1467	963
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	Not Changd	N/A
Filter Changed		Client Info		None	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>1250	219	285	706
Iron	ppm	ASTM D5185m	>750	427	401	373
Chromium	ppm	ASTM D5185m	>9	6	5	5
Nickel	ppm	ASTM D5185m	>10	2	0	0
Titanium	ppm	ASTM D5185m		1	0	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>40	7	4	2
Lead	ppm	ASTM D5185m	>15	0	0	0
Copper	ppm	ASTM D5185m	>40	3	0	<1
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION







There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	37	30	23
Potassium	ppm	ASTM D5185m	>20	5	2	11
Water		WC Method	>0.075	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	LIGHT	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>51	3	1	4
Boron	ppm	ASTM D5185m		72	94	83
Barium	ppm	ASTM D5185m		<1	0	3
Molybdenum	ppm	ASTM D5185m		0	6	0
Manganese	ppm	ASTM D5185m		9	7	7
Magnesium	ppm	ASTM D5185m		1	21	0
Calcium	ppm	ASTM D5185m		54	55	17
Phosphorus	ppm	ASTM D5185m		522	540	531
Zinc	ppm	ASTM D5185m		24	40	16
Sulfur	ppm	ASTM D5185m		18400	17461	14943
Visc @ 40°C	cSt	ASTM D445		184	187	188



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0225741 **Received** : 28 Jun 2024
Lab Number : 06223768 **Tested** : 01 Jul 2024
Unique Number : 11101965 **Diagnosed** : 01 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

B & S SITE DEVELOPMENT
 7800 PINEY BRANCH LANE
 BRISTOW, VA
 US 20136
 Contact: DANNY HUFF
 dhuff@bandssite.com
 T: (540)270-3203
 F: (703)753-0605

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)