

Area  
**ETS**  
Machine Id  
**[ETS] 66**  
Component  
**Diesel Engine**  
Fluid  
**PETRO CANADA DURON SHP 15W40 (24 QTS)**

**RECOMMENDATION**

We advise that you check for the source of the coolant leak. Check for low coolant level. Oil and filter change at the time of sampling has been noted. We recommend an early resample to monitor this condition.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>PCA0041874</b>	WC0843765	WC0788566
Sample Date		Client Info		<b>13 Jun 2024</b>	29 Dec 2023	12 Jul 2023
Machine Age	mls	Client Info		<b>318519</b>	312421	306024
Oil Age	mls	Client Info		<b>6098</b>	6397	6428
Filter Age	mls	Client Info		<b>6098</b>	6397	6428
Oil Changed		Client Info		<b>Changed</b>	Changed	Changed
Filter Changed		Client Info		<b>Changed</b>	Changed	Changed
Sample Status				<b>ABNORMAL</b>	ABNORMAL	SEVERE

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	<b>47</b>	34	46
Chromium	ppm	ASTM D5185m	>5	<b>&lt;1</b>	1	2
Nickel	ppm	ASTM D5185m	>4	<b>&lt;1</b>	<1	<1
Titanium	ppm	ASTM D5185m	>2	<b>&lt;1</b>	<1	<1
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>15	<b>4</b>	4	3
Lead	ppm	ASTM D5185m	>25	<b>2</b>	1	1
Copper	ppm	ASTM D5185m	>100	<b>0</b>	1	<1
Tin	ppm	ASTM D5185m	>4	<b>&lt;1</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**













Sodium and/or potassium levels remain high.

Silicon	ppm	ASTM D5185m	>25	<b>12</b>	7	18
Potassium	ppm	ASTM D5185m	>20	<b>▲ 193</b>	▲ 262	▲ 881
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol	%	*ASTM D2982		<b>NEG</b>	NEG	▲ 0.20
Soot %	%	*ASTM D7844	>6	<b>0.5</b>	0.4	0.5
Nitration	Abs/cm	*ASTM D7624	>20	<b>12.0</b>	11.2	14.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>23.1</b>	22.2	25.5
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**

The BN result indicates that there is suitable alkalinity remaining in the oil.

Sodium	ppm	ASTM D5185m		<b>▲ 61</b>	▲ 90	● 309
Boron	ppm	ASTM D5185m	0	<b>5</b>	3	10
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	60	<b>77</b>	75	132
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	<1
Magnesium	ppm	ASTM D5185m	1010	<b>1101</b>	959	1034
Calcium	ppm	ASTM D5185m	1070	<b>1224</b>	1063	1232
Phosphorus	ppm	ASTM D5185m	1150	<b>1178</b>	1068	1094
Zinc	ppm	ASTM D5185m	1270	<b>1456</b>	1223	1399
Sulfur	ppm	ASTM D5185m	2060	<b>3716</b>	2970	4149
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>20.1</b>	19.2	21.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>8.68</b>	7.4	7.3
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.1</b>	12.8	12.95



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : PCA0041874 **Received** : 28 Jun 2024  
**Lab Number** : 06224084 **Tested** : 02 Jul 2024  
**Unique Number** : 11102281 **Diagnosed** : 02 Jul 2024 - Jonathan Hester  
**Test Package** : MOB 2 ( Additional Tests: Glycol )

**HUMBOLDT TRANSIT AUTHORITY**  
 133 V ST  
 EUREKA, CA  
 US 95501  
 Contact: KELLY MASTERSON  
 kelly@hta.org  
 T:  
 F:

Certificate L2367  
 To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)