

Machine Id BAUER BG 39 4160363 - TRAIN Component Final Drive

SHELL OMALA 220 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION


There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0825173		
Sample Date		Client Info		21 May 2024		
Machine Age	hrs	Client Info		7105		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		Changed		
Sample Status				NORMAL		
Iron		ASTM D5185m	>500	39		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	0 <1		
Titanium	ppm	ASTM D5185m	>10	0		
Silver	ppm	ASTM D5185m		-		
Aluminum	ppm		► OF	0		
Lead	ppm	ASTM D5185m ASTM D5185m	>25 >25	2 <1		
	ppm					
Copper	ppm	ASTM D5185m	>50	0		
Tin Vanadium	ppm	ASTM D5185m	>10	<1 0		
White Metal	ppm	*Visual	NONE	-		
	scalar			NONE		
Yellow Metal	scalar	*Visual	NONE			
Silicon	ppm	ASTM D5185m	>75	29		
Potassium	ppm	ASTM D5185m	>20	2		
Water		WC Method	>0.2	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Sodium		ASTM D5185m		0		
Boron	ppm	ASTM D5185m	4.4	7		
Barium	ppm ppm	ASTM D5185m	4.4 0.0	0		
Molybdenum	ppm	ASTM D5185m	0.0	0		
Manganese	ppm	ASTM D5185m	0	1		
Magnesium		ASTM D5185m	0	0		
Calcium	ppm	ASTM D5185m	0	۰ <1		
Phosphorus	ppm ppm	ASTM D5185m	215	463		
Zinc	ppm	ASTM D5185m	0	403 17		
Sulfur	ppm	ASTM D5185m	7039	3945		
Visc @ 40°C		ASTM D3185ml	220	212		
	cSt	ASTIVI D445	220	212		

Contact/Location: CHARLIE JOHNS - HAYHOUTX



Ferrous Alloys 40 21 30 25 ظ 20 15 10 0 Non-ferrous Metals 10 lead maa Viscosity @ 40°C 270 Ał 260 250 240 230 <u>ှ</u> 220 र्दे २१० 200 190 180 170 160 May21/24 Mav21/24



KELLER - HOUSTON Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : WC0825173 Received : 28 Jun 2024 15410 HENRY RD Lab Number : 06224121 Tested HOUSTON, TX : 01 Jul 2024 Unique Number : 11102318 Diagnosed : 01 Jul 2024 - Angela Borella US 77060 Test Package : CONST Contact: CHARLIE JOHNS To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (281)931-4972

Certificate L2367

Contact/Location: CHARLIE JOHNS - HAYHOUTX Page 2 of 2